Lawrence Berkeley National Laboratory

Recent Work

Title

TEMPERATURE DEPENDENCE OF THE WAVELENGTH MODULATION SPECTRA OF GaAs

Permalink

<https://escholarship.org/uc/item/8sk7q3gg>

Authors

Walter, John P.
Zucca, Ricardo R.L.
Cohen, Marvin L.
et al.

Publication Date

1969-10-01

RECEIVED
JAN 14 1970
LIBRARY AND
DOCUMENTS SECTION

JAN 14 1970

LIBRARY AND
DOCUMENTS SECTION

TEMPERATURE DEPENDENCE OF THE WAVELENGTH
MODULATION SPECTRA OF GaAs

John P. Walter, Ricardo R. L. Zucca, Marvin L. Cohen
and Y. R. Shen

October 1969

AEC Contract No. W-7405-eng-48

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

UCRL-19118
ay.2

LAWRENCE RADIATION LABORATORY
UNIVERSITY of CALIFORNIA BERKELEY

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

UNIVERSITY OF CALIFORNIA

Lawrence Radiation Laboratory
Berkeley, California

AEC Contract No. W-7405-eng-48

TEMPERATURE DEPENDENCE OF THE WAVELENGTH
MODULATION SPECTRA OF GaAs*

John P. Walter,[†] Ricardo R. L. Zucca,[‡] Marvin L. Cohen[§]

and Y. R. Shen

October 1969

* Supported in part by the National Science Foundation

[†] National Science Foundation Graduate Fellow

[‡] Fellow, Consejo Nacional de Investigaciones Cientificas y Tecnicas, Argentina

[§] Miller Institute Professor 1969-70

Temperature Dependence of the WavelengthModulation Spectra of GaAs*

by

John P. Walter,[†] Ricardo R. L. Zucca,[‡] Marvin L. Cohen,[§]
and Y. R. Shen

Department of Physics and Inorganic Materials Research Division,
Lawrence Radiation Laboratory, University of California
Berkeley, California 94720

ABSTRACT

Wavelength modulation spectroscopy is used to obtain the temperature dependence of the reflectivity spectrum for GaAs. Results are given in the regions of the E_1 doublet and the major E_2 peak at 5, 80, 150, 225, and 300°K. The theoretical temperature dependence in these regions is obtained through using Debye-Waller factors and thermal expansion coefficients in an empirical pseudopotential calculation of the $(\Lambda_3-\Lambda_1)$ and $(\Sigma_2-\Sigma_1)$ energy splittings.

*Supported in part by the National Science Foundation

†National Science Foundation Graduate Fellow

‡Fellow, Consejo Nacional de Investigaciones Cientificas y Tecnicas, Argentina

§Miller Institute Professor 1969-70

We have measured the derivative of the reflectivity for GaAs using a wavelength modulation technique. Results are given in the vicinity of the E_1 and E_2 reflectivity peaks at 5, 80, 150, 225, and 300°K. (Figure 1). This is the first report of a derivative spectrum which has been accurately measured over a wide temperature range, and of a successful theoretical calculation of the temperature dependence of the reflectivity structure at and above the fundamental gap.

Wavelength modulation is achieved through the vibration of a mirror in the optical path inside the spectrometer. A two-beam method with appropriate electronics is used to eliminate the background noise and to yield a derivative reflectivity spectrum $R'(\lambda)/R(\lambda)$ of the sample. This output is converted to the functional form $R'(\omega)/R(\omega)$. The sample is a single crystal of n-type GaAs with a carrier concentration of 10^{16} cm^{-3} . After the sample is freshly polished and etched, it is mounted within an optical dewar, in which the temperature can be varied continuously from 4°K to 300°K, with an accuracy of $\pm 1^\circ\text{K}$. The detailed construction of our wavelength modulation spectrometer and associated experimental equipment is described elsewhere.⁽¹⁾

The wavelength modulation spectra for the five temperatures in the regions of the E_1 doublet peak and the E_2 major peak are shown in Fig. 1. The positions of the peaks and valleys of the reflectivity are given by the zeroes of the modulated spectra. The temperature shifts of the E_1 and E_2 peaks are plotted in Figure 2.

To calculate the theoretical temperature dependence of the GaAs spectrum, it is necessary to know the electronic band structure, the transitions which cause the reflectivity peaks, the thermal expansion

function, and the phonon spectrum of the crystals. The band structure of GaAs is obtained by the empirical pseudopotential method,⁽²⁾ with spin-orbit effects included.⁽³⁾ The pseudopotential form factors used are $v^S(G^2=3) = -0.2460$, $v^S(8) = -0.0008$, $v^S(11) = 0.0737$, $v^A(3) = 0.583$, $v^A(4) = 0.0509$, and $v^A(11) = 0.0011$ Ry.⁽⁴⁾ The form factors for $G^2 > 11$ are constrained equal to zero. The spin-orbit parameter is adjusted so that the spin-orbit splitting at Γ is 0.35 eV. The E_1 doublet is caused by $\Lambda(4-5)$ and $\Lambda(3-5)$ transitions, and the E_2 peak is caused by $\Sigma(4-5)$ transitions.^(4,5) The theoretically calculated peaks occur at the same energies as the $\Lambda(4-5)$ and $\Lambda(3-5)$ transitions, and the positions of these peaks, in turn, agree with the experimentally determined positions. For the E_2 peak the agreement is not as good; the theoretically calculated E_2 peak is 0.17 eV below the corresponding experimental peak. In addition, the Σ critical point is 0.06 eV below the theoretical E_2 peak. Consequently, the theoretically calculated Σ critical point lies 0.23 eV below the experimental E_2 peak. We have therefore introduced a corresponding shift in Figure 2, since it is the temperature dependence of the Σ critical point that is actually calculated.

The principal factors governing the temperature dependence of the reflectivity spectrum are the thermal expansion of the crystal and the thermal vibrations of the nuclei (the Debye-Waller effect). Since an expanded lattice reduces the average potential seen by an electron, the energy splittings between the bands are generally smaller⁽⁶⁾ at higher temperatures and the positions of the reflectivity peaks shift to lower energies. The temperature dependence of the lattice constant is obtained from the thermal expansion function for GaAs.⁽⁷⁾ The lattice constants used at 5, 80, 150, 225, and 300°K are 5.640, 5.640, 5.641, 5.643, and 5.645 Å, respectively. Since both the volume of the unit cell and the values of the reciprocal lattice vectors change

slightly with variations in the lattice constant, we must necessarily scale the pseudopotential form factors, the criterion being that the actual atomic potentials remain unchanged.

The thermal vibrations of the nuclei reduce the effective atomic potentials by the Debye-Waller factor e^{-W} .⁽⁸⁾ Like the thermal expansion effect, the Debye-Waller effect reduces the energy splittings and causes the reflectivity peaks to shift to lower energies. The Debye-Waller factor can be calculated from the experimental phonon spectrum, and since this calculation is greatly simplified for a monatomic crystal, we have used the phonon spectrum of germanium instead of GaAs. This is a reasonable approximation because the GaAs phonon spectrum is nearly identical to that of germanium, and the average density of GaAs is the same as that of germanium to within 0.5%. Accordingly, we use an expression given by Blackman⁽⁹⁾ for a monatomic crystal:

$$W = \frac{hG^2}{8\pi^2 m} \frac{\int \rho(\nu) \nu^{-1} \left[\frac{1}{2} + \frac{1}{e^x - 1} \right] d\nu}{\int \rho(\nu) d\nu} \quad (1)$$

where $x = h\nu/kT$, $\rho(\nu)$ is the density of phonon modes for Ge,⁽¹⁰⁾ G is a reciprocal lattice vector, and m is the mass of the nucleus. The values of (W/G^2) we obtain by using Eq. (1) at 5, 80, 150, 225, and 300°K are 0.0010, 0.0015, 0.0024, 0.0034, and 0.0044, respectively.⁽¹¹⁾ Using X-ray measurements on germanium, Batterman and Chipman⁽¹²⁾ obtain a value of $(W/G^2) = 0.0043$ at 300°K.

The Debye-Waller and lattice expansion effects are incorporated in a pseudopotential calculation of the band structure to give the temperature shifts of selected transitions in the Brillouin zone. In Table I, the result-

ing theoretical temperature dependence at Γ (the fundamental gap) is compared to the experimental temperature dependence obtained by Oswald⁽¹³⁾ and by Sturge.⁽¹⁴⁾ The calculated result at Γ agrees closely with that of Oswald. The Debye-Waller and lattice expansion effects can be calculated separately to show that the major part of the energy shift is caused by Debye-Waller effect, with only a small fraction caused by lattice expansion. At Γ the total calculated energy change between 5° and 300°K is -0.158 eV, of which -0.020 eV is caused by lattice expansion, or about 13% of the total.

An additional check on the accuracy of theoretical calculations using this pseudopotential band structure is provided by a calculation of the variation of the fundamental gap with respect to a slight change in the lattice constant. This calculation gives a value of $V\left(\frac{\partial E}{\partial V}\right)_T = -7$ eV, a result which agrees exactly with the experimentally measured value.⁽¹⁵⁾

The theoretical temperature dependence of the $\Lambda(4-5)$, $\Lambda(3-5)$, and $\Sigma(4-5)$ transitions is shown in Figure 2. The comparison between theory and experiment for the E_2 peak is good, and for the E_1 doublet the comparison is excellent.

The temperature shifts of the reflectivity peaks in GaSb, InAs, and InSb are found to be approximately of the same magnitude as in GaAs.⁽¹⁾ We expect that similar theoretical calculations of the temperature dependence in these crystals would also yield good results.

ACKNOWLEDGEMENTS

This work was done under the auspices of the U.S. Atomic Energy Commission.

References

1. R. R. L. Zucca and Y. R. Shen, to be published.
2. M. L. Cohen and T. K. Bergstresser, Phys. Rev. 141, 789 (1966);
J. P. Walter and M. L. Cohen, Phys. Rev. 183, 763 (1969).
3. S. Bloom and T. K. Bergstresser, Solid State Comm. 6, 465 (1968).
4. R. R. L. Zucca, J. P. Walter, Y. R. Shen and M. L. Cohen, to be published.
5. The notation refers to critical point transitions in the Brillouin zone. The bands are numbered consecutively, the fourth band is the highest valence band, and the fifth band is the lowest conduction band.
6. This is not the case for the lead salts; e.g. see C. Keffer, T. M. Hayes and A. Bienenstock, Phys. Rev. Letters 21, 1676 (1968), and Y. W. Tsang and M. L. Cohen, to be published.
7. S. I. Novikova, Soviet Physics--Solid State 3, 129 (1961).
8. S. C. Yu, Ph.D. Thesis, Harvard (1964).
9. M. Blackman, Handbuch der Physik VI, Sec. 1, 325 (1955).
10. J. C. Phillips, Phys. Rev. 113, 147 (1959).
11. G is in units of $(2\pi/a)$.
12. B. W. Batterman and D. R. Chipman, Phys. Rev. 127, 690 (1962).
13. F. Oswald, Z. Naturforsch. 10a, 927 (1955).
14. M. D. Sturge, Phys. Rev. 127, 768 (1962).
15. W. Paul, J. Appl. Phys. Suppl. 32, 2082 (1961).

Captions

Table I: Fundamental gap of GaAs as function of temperature.

Experiment 1 is due to F. Oswald (Ref. 13). Experiment 2 is due to M. D. Sturge (Ref. 14).

Figure 1: Plots of $R'(\omega)/R(\omega)$ in the regions of the E_1 doublet peak and the E_2 major peak. Plots 1 through 5 refer to temperatures of 5° , 80° , 150° , 225° , and 300°K , respectively.

Figure 2: Plots of the explicit temperature dependence of the experimental E_1 and E_2 reflectivity peaks and of the corresponding theoretically calculated $\Lambda(4-5)$, $\Lambda(3-5)$, and $\Sigma(4-5)$ transitions.

Table I

Temperature ($^{\circ}$ K)	Theory (eV)	Experiment 1 (eV)	Experiment 2 (eV)
5	1.52	1.53	1.52
80	1.50	1.49	1.51
150	1.46	1.45	1.49
225	1.41	1.42	1.46
300	1.36	1.38	1.43

Figure 1

UCRL-19118

Figure 2

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or*
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.*

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

3 - 4 - 3

TECHNICAL INFORMATION DIVISION
LAWRENCE RADIATION LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720

7