UC Davis

UC Davis Previously Published Works

Title

Development of Improved Double-Nanobody Sandwich ELISAs for Human Soluble Epoxide Hydrolase Detection in Peripheral Blood Mononuclear Cells of Diabetic Patients and the Prefrontal Cortex of Multiple Sclerosis Patients.

Permalink

<https://escholarship.org/uc/item/8xc3108k>

Journal

Analytical chemistry, 92(10)

ISSN

0003-2700

Authors

Li, Dongyang
Morisseau, Christophe
McReynolds, Cindy B
et al.

Publication Date

2020-05-01

DOI

10.1021/acs.analchem.0c01115

Peer reviewed

Design and fabrication of a highly sensitive and naked-eye distinguishable colorimetric biosensor for chloramphenicol detection by using ELISA on nanofibrous membranes

Cunyi Zhao^a, Yang Si^a, Bofeng Pan^a, Ameer Y. Taha^b, Tingrui Pan^c, Gang Sun^{a,*}

^a Biological and Agricultural Engineering, University of California, Davis, CA, 95616, USA

^b Food Science and Technology, University of California, Davis, CA, 95616, USA

^c Biomedical Engineering, University of California, Davis, CA, 95616, USA

ARTICLE INFO

Keywords:

Enzyme-linked immunoassay
Nanofibrous membrane
Enzyme-linked immunosorbent assay
Chloramphenicol
Naked-eye distinction
Colorimetric sensor

ABSTRACT

Enzyme-linked immunoassay (ELISA) is highly specific and selective towards target molecules and is convenient for on-site detection. However, in many cases, lack of high sensitivity makes it hard to reveal a significant colorimetric signal for detecting a trace amount of target molecules. Thus, analytical instruments are required for detection, which limits the application of ELISA for on-site detection. In the present study, a highly sensitive and naked-eye detectable colorimetric biosensor for chloramphenicol (CAP) was prepared by incorporating ELISA onto surfaces of microporous and nanofibrous membranes. The high specific surface areas of the nanofibers significantly increased the number of antibodies covalently linked onto the fiber surfaces and binding capacity of the sensor with antigens present in a sample. With such an integration, the sensitivity of the ELISA sensor was dramatically increased, and a trace number of targets could reveal a naked-eye detectable color. The immunoassay sensor exhibited a significant naked-eye distinguishable color to chloramphenicol (CAP) at 0.3 ng/mL. The successful design and fabrication of the nanofibrous membrane immunoassay sensor provide new paths towards the development of on-site inspection sensors without the assistance from any instrument.

1. Introduction

Antibiotics are widely applied in the medical treatments of human infections and prevention of diseases in stock and aquaculture farming [1–3]. Due to their broad applications in agriculture and aquaculture production, residual antibiotics could exist in food products [3,4]. Frequent exposure to residual antibiotics could lead to the development of antibiotic-resistant bacteria. Approximately 2 million people acquire infections caused by antibiotic-resistant pathogens each year in the United States [5]. The cost associated with antibiotic-resistant bacterial treatments has doubled over the past few decades and reached \$2 billion in 2014 [5]. As a result, the United States Department of Agriculture (USDA) and the US Food and Drug Administration (FDA) have established strict regulations on tolerant concentrations for specific antibiotics in aquaculture and farmed products. Although precise and selective measurements of antibiotics are available by mass-spectrometry, their routine analysis is currently cost-prohibitive due to the complexity of the analytical methods involved. Thus, rapid, accurate, and on-site detection is needed to track residual antibiotics in the food

supply.

The standard detection methods for antibiotics in foods include Liquid Chromatography or Gas Chromatography-Mass Spectrometry (LC/GC-MS) and Enzyme-Linked Immunosorbent Assay (ELISA) [6,7]. The LC/GC-MS is a reliable, sensitive, and selective technique but has limitations such as the use of expensive apparatus, complicated procedures, the need of trained operators, and long preparation time, which limit their uses in on-site inspections and instant examinations [8,9]. Contrarily, ELISA is a relatively convenient analytical technique with good selectivity. However, the conventional ELISA could not generate naked-eye distinguishable color at low concentration of the target analyte. The conventional ELISA process is also dependent on the use of plate readers or instruments to detect targets in low concentrations, which limits its application for on-site detection of a trace number of targets [10–15]. For achieving naked-eye detection, the color intensity needs to be significantly improved, and some successful approaches were made by using gold nanoparticles, quantum dots, new antibodies or nanobodies with high affinity to solid surfaces [12–15]. However, these processes are relatively costly and time-consuming with

* Corresponding author.

E-mail address: gysun@ucdavis.edu (G. Sun).

<https://doi.org/10.1016/j.talanta.2020.121054>

Received 1 December 2019; Received in revised form 14 April 2020; Accepted 16 April 2020

Available online 18 April 2020

0039-9140/© 2020 Elsevier B.V. All rights reserved.

limited improvement of sensitivities. To meet the demand for on-site and instrument-independent detection, we report the development of a highly sensitive and naked-eye distinguishable paper-based ELISA biosensor by employing microporous and nanofibrous membranes as solid support media for antibodies. The ultrahigh surface areas of the nanofibers in the paper-like membranes could dramatically increase the number of immobilized antibodies incorporated onto the surfaces, which can quickly capture analytes in the environment, leading to dramatically intensified colorimetric signals enough for human eye detection. In this study, we focused on chloramphenicol (CAP) because it is banned in the USA but may be still present in some imported US aquaculture products [5]. The developed immunoassay biosensor demonstrated high sensitivity for detecting CAP at 0.3 ng/mL level with the naked eyes, compared to the 10 ng/mL of CAP distinguishable by the naked eye with a conventional ELISA.

2. Materials and methods

2.1. Materials

Glutaraldehyde solution 25% (GA), cyanuric chloride (CC), N, N'-disuccinimidyl carbonate (DSC), triethylamine (TEA), 1,4-dioxane, acetone, hydrogen peroxide (30 wt%), pH 6.4 citric acid buffer, phosphate-buffered saline (PBS), Pierce™ BCA Protein Assay Kit, Millipore column and high-binding 96-well plates were purchased from Thermo Fisher Scientific (USA). Poly(vinyl-co-ethylene) (PVA-co-PE, PE content of 27%, MWn = 90,000), chloramphenicol (CAP), florfenicol (FF), thiamphenicol (TAP), penicillin (PCN), 3,3',5,5'-tetramethylbenzidine (TMB), fluorescein isothiocyanate labelled immunoglobulin G (FITC-IgG), and bovine serum albumin (BSA) were obtained from Sigma-Aldrich (USA). Anti-CAP antibody (Ab) and CAP labelled horseradish peroxidase (CAP-HRP) were purchased from Abcam (Cambridge, MA, USA). Nitrocellulose membrane (0.45 μm) was purchased from Bio-Rad (USA).

2.2. Fabrication of PVA-co-PE nanofibrous membranes

PVA-co-PE nanofibrous membrane was fabricated according to the literature [16,17]. PVA-co-PE (Mn = 90,000) was added into a mixture of isopropanol and water (weight ratio 7:3) with stirring at 80 °C for 2 h to prepare electrospinning solutions. The concentration of PVA-co-PE in the electrospinning solution was 8 wt%. Then, the solution was transferred into 20 mL syringes, capped by a 6-gauge needle and loaded onto a programmable syringe pump (Kats Scientific Co.). The solution was fed at a constant rate of 2 mL per hour. A high voltage of 25 kV (EQ30, Matsusada Inc.) was employed on needle tips generating a continuous polymer jet stream. The PVA-co-PE nanofiber membranes were deposited on a copper grid covered the rotating receiver with a fixed distance of 20 cm. Residual isopropanol/water solvent was removed by drying the produced nanofibrous membranes in a vacuum oven at 50 °C for 1 h.

2.3. Modification of nanofibrous membranes

For CC modified nanofibrous membranes, 0.1g of PVA-co-PE nanofibrous membranes were immersed into 3M NaOH aqueous solution at 5 °C for 30 min and then were immersed into 0.1 g/mL CC solution (prepared by dissolving 5g CC in 50 mL of 1,4-Dioxane) at room temperature for 2 h. The resulting membranes were removed out, washed with water and acetone, and vacuum dried. For GA modified membranes, 50 mL of 25 wt% GA aqueous solution was prepared, and then 0.1g of PVA-co-PE nanofibrous membranes were immersed into the GA solution at room temperature for 2 h. The resulting membranes were washed with water and acetone, and vacuum dried. For DSC modified membranes, 5 g of DSC and 0.2 g TEA were dissolved in 50 mL of 1,4-dioxane solvent, then 0.1 g PVA-co-PE membranes were added into this

as-prepared solution. The mixture was stirred at 80 °C for 2 h. The resulting membranes were washed with 1,4-dioxane and acetone, and vacuum dried.

2.4. Immobilization of antibody

The antibody stock solution was diluted to concentrations of 0.1 g/L, 1 g/L, and 2 g/L in PBS buffer. Then, 10 μL of each antibody solution was dropwise added to the center of a pre-punched 1 cm² modified PVA-co-PE membrane. The membranes were incubated into a bio-oven at 25 °C for 20 min. After that, unreacted antibodies on the membranes were washed-off with PBS buffer. The number of the immobilized proteins was determined by the bicinchoninic acid (BCA) protein assay via UV-vis spectroscopy in three replicates for each experiment. The absorption intensity at wavelength 562 nm was recorded to obtain the number of antibodies on the membrane. The protein immobilization reaction efficiency was calculated by dividing the number of immobilized proteins by the number of injected proteins. The resulting membranes were immersed into a 1 wt% BSA solution to block any unreacted sites and rinsed by a washing buffer (PBS solution containing 0.05% Tween 20) to remove excess unbound proteins.

2.5. Analysis of colorimetric signals from ELISA

A competitive ELISA assay was used to detect antibiotics. A test solution was prepared by mixing 50 μL of CAP solution at varying concentrations (ranging between 0 ng/mL to 100 ng/mL) with 50 μL of 500 ng/mL CAP-HRP. Then, the antibody immobilized membranes were exposed to the mixture solution under gentle agitation for 20 min. The membranes were then washed with the PBS buffer and dried in air. A TMB substrate was prepared by mixing 100 μL of 0.6 wt% TMB solution, 25 μL of 1 wt% H₂O₂ aqueous solution, and 6.25 mL of citric acid buffer, together. 20 μL of the as-prepared TMB substrate was added onto the membranes, and the membranes were placed in an LED lightbox (E mart) for 15 min. A colorimetric signal was observed under the LED light (Lux 10,000). The colorimetric signal was captured by a smartphone (iPhone 6s) and quantitatively analyzed by Image J software. The smartphone camera was kept at the top of nanofibrous membranes at a fixed distance of 50 cm to record digital images of the membranes. The red, green, and blue values (RGB values) in the red channel (R value) could be scanned by an installed imaging app (ColorAssist) after transferring digital images to a computer. Moreover, the R values were utilized to analyze the concentration of CAP. The sample size is three for all experiments.

2.6. Analysis of colorimetric signals from conventional ELISA

The CAP solutions in varied concentrations were analyzed by both 96-wells plate-based and nitrocellulose membrane-based ELISAs, respectively. The antibody solution was diluted to concentrations of 2 g/L and was added to each well or each membrane, respectively. The samples were incubated in a bio-oven at 37 °C for 1 h. Then, the procedures of blocking, rinsing, and addition of a test solution and TMB substrate were conducted as described in experimental section 2.5. The absorbance intensity of 96-wells plate-based ELISA was recorded by a microplate reader (ThermoFisher Inc.). A smartphone (iPhone 6s) was used to analyze the colorimetric signal from the nitrocellulose membrane-based ELISA.

2.7. Test of salmon sample

Salmon samples were purchased from local supermarkets in Davis, CA. 1 g of salmon was mixed with 3 mL of PBS solution. The mixture was homogenized at a vortex oscillator and filtered by a Millipore column to remove solids and lipids [18]. Various concentrations of CAP were added into the filtered solution to make spiked samples.

Scheme 1. Design, fabrication, and work mechanism of nanofibrous membrane-based ELISA.

Subsequently, 50 μL of the filtrate was mixed with 50 μL of 500 ng/mL CAP-HRP to prepare a test solution, which was directly added to the functional nanofibrous membranes following the procedure described in section 2.5.

3. Results and discussion

3.1. Fabrication of nanofibrous membrane-based ELISA

In the present study, the incorporation of the antibody onto the surfaces of nanofiber membranes could increase sensitivity and produce color signals readable by naked eyes. Schematic design and workflow of the nanofiber membrane-based ELISA immunosensor is shown in Scheme 1. PVA-co-PE was selected as a polymer to produce nanofibrous membranes by electrospinning. The electrospinning process fabricates nano-size fiber and provides an ultra-high specific area for membranes. A scanning electron microscope (SEM) image of a PVA-co-PE nanofibrous membrane is shown in Fig. 1a, with an average fiber diameter of approximately 400 nm and micro-size pores (Fig. 1a and b). PVA-co-PE nanofibrous membranes were previously shown to provide desired

reactions with proteins [19]. Here, hydroxy groups on the material could be activated by GA, CC or DSC for immobilization of antibodies. (Fig. 1c).

The GA, CC, and DSC modified membranes possess different reactivities and hydrophilicity to interact with protein molecules. Among three reactive groups, CC is the least reactive and most hydrophobic one, while GA has medium reactivity and hydrophilicity, and DSC is the most reactive and most hydrophilic. Fourier-transform infrared spectroscopy (FTIR) proved successful incorporations of the reactive groups, based on an aldehyde peak of GA at 1722 cm^{-1} , triazine peak of CC at 1547 cm^{-1} , and carbonate peak of DSC at 1730 cm^{-1} (Fig. 1d). The chemically modified nanofibrous membranes retained the micro-porosity and nanofibrous structures (Fig. 1e), reflecting the structural stability of the nanofibrous membranes and ensuring proper applications in further steps of reactions with biomolecules. Here, the CC modified nanofibers became swollen and adhesive because of alkali treatment of the PVA-co-PE membranes. The original nanofiber diameter of 449.57 nm increased to 726.31 nm after the CC modification as shown in Fig. 1f. In contrast, the morphologies of the GA and DSC modified membranes were almost unchanged with the nanofiber

Fig. 1. Microstructure and chemical modifications of nanofibrous membranes. a) SEM and b) Fiber diameter distribution of PVA-co-PE membrane; c) Reaction schemes of PVA-co-PE membrane with three reagents (CC, GA, and DSC) and proteins; d) FTIR spectra of PVA-co-PE membranes before and after modifications of CC, GA, and DSC; e) SEM images and f) Fiber distributions of these nanofibrous membranes after reactions with CC, GA, and DSC; g) Water contact angles of these membranes.

diameter slightly increased to 532.51 nm and 547.19 nm, respectively. Additionally, the GA, CC, and DSC reagents on the surfaces of the fibers also improved hydrophilicity and wettability of PVA-co-PE fibers. The water contact angles of the membranes were measured after 1 s (1s) water contact as shown in Fig. 1g. The original membranes were relatively hydrophobic with a water contact angle of 89.8°. Since CC is a non-polar reagent, the slight improvement of the membrane hydrophilicity (a water contact angle at 72°) may be attributed to polymer swelling during alkali treatment. In contrast, the more polar reagents (GA and DSC) modified membranes exhibited improved hydrophilicity, with water contact angles at 31.1° and 22.8°, respectively. However, water could be fully adsorbed on the three modified membranes after 10s wetting time (0° water contact angle) (Fig. S1).

3.2. Immobilization of protein onto nanofibrous membranes

The three modified membranes were then employed to immobilize antibodies as shown in Fig. 1c. Here, FITC-IgG was used to qualitatively reveal the number of immobilized molecules by showing the intensities of fluorescence (brighter fluorescence indicates more immobilized proteins). The fluorescence images of each immobilized membranes are shown in Fig. 2a. FITC-IgG diffused more homogeneously into the more hydrophilic DSC and GA membranes than into the CC modified ones. An increase of the FITC-IgG solution concentration also improved the number of immobilized proteins on the CC membranes but not on the GA and DSC membranes because the accessible reactive sites of the GA and DSC modified membranes were likely saturated.

The number of immobilized antibodies and reaction efficiencies were quantitatively measured by the bicinchoninic acid assay (BCA) test (Fig. 2b and c). The CC modified membranes exhibited the lowest number of immobilized proteins, which was caused by the hydrophobic property and lower reactivity of the CC groups. Conversely, the hydrophilic and highly reactive reagents, GA and DSC, showed increased numbers of immobilized proteins on the membranes. Besides, the CC

modified membranes exhibited relatively low efficiency (20%). Contrarily, the immobilization efficiency on the GA and DSC treated membranes reached around 100% at low FITC-IgG concentration but dramatically decreased with the protein concentration increased, which confirmed the speculation that the reactive sites on these modified membranes were saturated. To compare the performance of the reagents, the number of immobilized antibodies should be the same on each membrane. Thus, a concentration of 1 g/L proteins was used in the immobilization reaction on the CC membranes, and a concentration of 0.5 g/L proteins was applied to the GA or DSC membranes.

Lastly, the impact of the immobilization reactions on the morphology of the nanofibrous membranes was studied by using an SEM, as shown in Fig. 2d. Compared with SEM images in Fig. 1e, all fibers of three membranes became a little more swollen after being immobilized with the bio-macromolecule, but still stayed nanofiber sizes, which can be described by the slight changes of fiber diameter distributions as shown in Fig. 2e.

3.3. Competitive ELISA on the nanofibrous membrane

Antibodies of CAP were immobilized on the chemically modified nanofibrous membranes, and the membranes were employed to detect CAP. The detection procedure is schematically described in Scheme 1. To find a proper concentration of CAP-HRP solution to be added onto the membranes, a checkerboard test was applied as shown in Fig. S2. A concentration of CAP-HRP at 250 ng/mL was identified as the optimal concentration.

Color signals could be observed under different concentrations of CAP solutions containing 250 ng/mL of CAP-HRP with various exposure times (Fig. 3). TMB was used as an indicator of hydrogen peroxide generation via the catalytic effect of the peroxidase (CAP-HRP) enzyme. The oxidized TMB compound reveals a blue color (absorbance wavelength locates at 605 nm), with intensity of the blue color indicating the number of CAP-HRPs conjugated with the antibodies on

Fig. 2. Immobilizing antibody onto nanofibrous membranes. a) Fluorescence images of three modified membranes immobilized with FITC-IgG; b) Immobilized antibody amounts on modified membranes; c) Immobilization reaction efficiency; d) SEM images of nanofibrous membranes after immobilization with the antibody; e) Fiber distributions of these membranes.

Fig. 3. Optical images and color intensities (R values) of membranes modified by a) CC; b) GA; and c) DSC in the detection of CAP. (For interpretation of the references to color in this figure legend, the reader is referred to the Web version of this article.)

the membranes. The red channel value (R value) from red, green, and blue (RGB) results shows the most significant change from the readings obtained with the smartphone. Thus, an R value was employed to represent the color intensity, with a lower R value indicating higher CAP concentration. As shown in Fig. 3a, colorimetric signals were not homogenous on the CC modified membranes, causing relatively high error bars on R values in the plots. The blue color almost disappeared on the CC membranes at a low concentration of CAP at 0.3 ng/mL. The R value of the color signal reached a maximum value at 0.3 ng/mL with 45 units higher than the R value at 0 ng/mL and 30 units higher than that at 0.2 ng/mL. These differences were easily visible by the naked eyes. On the contrary, although the GA and DSC treated membranes presented homogenous color signals (lower error bars), they could only distinguish higher CAP concentrations (0.5 ng/mL by the GA modified membranes and 1 ng/mL by the DSC modified membranes, respectively). Furthermore, the R values measured on the GA or DSC modified membranes could not achieve the maximum (155 units) at 1 ng/mL of CAP because a considerable number of CAP-HRPs was likely bound to the immobilized antibodies on the membranes. The CAP molecules seem to have better competitive ability than CAP-HRP molecules with the antibody on the CC modified membranes, which is likely due to the conformation change after immobilization. For example, the conformation of the loaded antibody may be affected by the membranes, and loaded antibody on CC membranes has a higher affinity with CAP than CAP-HRP. Therefore, more CAP could be captured on the CC modified membranes, and the sensitivity of the membrane was the highest. In general, all three membranes demonstrated varied abilities to detect trace amounts of CAP in solution, with the CC modified membranes showing the highest sensitivity in the applications and being considered as the best substrate for the preparation of naked eye readable colorimetric sensors for CAP detection.

Besides, the exposure time also influences the sensitivity. The oxidation of TMB by hydrogen peroxide and CAP-HRP is slow at the beginning of the reaction, due to a lower concentration of generated hydroxyl radicals, and becomes faster with the increase in reaction time, and gradually slows down again when the reagents are consumed. Thus, a membrane that captured more CAP-HRPs (less CAP) should reveal a brighter color more rapidly than a membrane containing fewer CAP-HRPs (more CAP) in a short reaction duration. Finally, all membranes should exhibit the same color intensity at the end of the reaction

theoretically because the same number of TMB molecules were added. The CC modified membranes revealed distinct color change, as well as with significant R value differences, for solutions containing 0.2 ng/mL and 0.3 ng/mL CAP at a reaction time of 5mins, and the difference became more significant at 15mins. In contrast, the GA modified membranes exhibited a fast reaction with TMB, producing a more significant color difference within a short time (5mins) than at long reaction time (15mins). The corresponding R value difference between 0.2 ng/mL and 0.3 ng/mL was around 30 units at 5mins but decreased to 20 at 15mins. More CAP-HRPs on the GA-modified membranes prompted faster and possibly more sustained oxidation reaction of TMB, which could also explain why the color signal difference between 0.3 ng/mL and 0.5 ng/mL became significant with reaction time increase on the GA treated membranes. For the best use of the sensors in on-site detection for naked-eye observation, the color difference for a detectable range of a target should be significant and consistent for a reasonable duration. Hence, the GA treated membranes can be used for sensors to detect 0.5 ng/mL CAP but may not be suitable to distinguish 0.3 ng/mL CAP. Similarly, the sensors made from the DSC treated membranes would be useful in the detection of higher CAP concentration because the color difference between 0.5 ng/mL and 1 ng/mL of CAP became less significant.

3.4. Understanding naked-eye distinguishable sensor

By using microporous and nanofibrous membranes as solid media for ELISA assay, we achieved the goal of developing highly sensitive colorimetric sensors for the antibiotic, CAP. A calibration curve of color intensity difference between the control and sample groups was established based on the following equation, and the results are presented in Fig. 4.

$$\frac{B}{B_0} = \frac{(R_{\max} - R_x)}{(R_{\max} - R_0)}$$

Here, B/B_0 represents the ratio of colorimetric intensity. $R_{\max}$ is the maximum R value, R_x is R value at specific CAP concentration, and R_0 represents the R value at 0 ng/mL of CAP. A higher ratio represents the concentration of CAP close to 0 ng/mL of CAP, and a lower ratio means more CAP in solutions. The concentrations of CAP varied from 0.01 ng/mL to 100 ng/mL in the calibration curve (Fig. 4). Thus, the

Fig. 4. Competitive ELISA intensity ratio. Color intensity ratios are plotted against CAP concentration. (For interpretation of the references to color in this figure legend, the reader is referred to the Web version of this article.)

concentration of CAP in a solution was quantitatively measured by determining the color intensity and deriving it from the calibration curve. The limit of detection (LOD) was 0.1 ng/mL, and the linear range was located between 0.1 ng/mL to 0.4 ng/mL. The linear relation equation could be described as $B/B_0 = (-140.2) \cdot \log(\text{Concentration of CAP}) - 54.5$ ($R^2 = 0.989$). The narrow linear range may be due to the color intensity recorded by RGB value rather than optical density with the conventional ELISA. Furthermore, if the linear range is properly extended, the LOD could decrease.

Besides the LOD and linear range, the lowest naked-eye distinguishable concentration is also a critical factor for portable devices, especially where it is not convenient to use smartphones or cameras. For example, although 0.1 ng/mL of CAP could be detected and concentrations below 0.3 ng/mL could be measured quantitatively, the membranes treated with low concentrated CAP could only reveal a slight color change which is hardly distinguished by naked eyes. The color changes of sensors at a benchmark concentration, such as a

government regulation limit, should be the most significant and confirmative to the naked eyes. Based on the optical images shown in Fig. 3a and the plot in Fig. 4, we estimated that at the benchmark concentration of 0.3 ng/mL CAP, the CC treated membrane could result in a blue color change significant enough for the naked eyes.

Then we compared the performance of nanofibrous membrane-based ELISA with other ELISA devices. Here, a 96 well plate was applied as a support media for commercial ELISA, and a nitrocellulose membrane was applied as a support media for conventional paper-based ELISA (Fig. 5). The concentrations of antibody and CAP-HRP were optimized based on checkerboard test results (shown in supplement information Figs. S3 and S4). Although UV-vis absorbance intensity from 96-wells plate-based ELISA represented the LOD at 0.1 ng/mL, the naked-eye distinguishable color change could only be observed between 1 ng/mL and 10 ng/mL of CAP (Fig. 5a). Meanwhile, the conventional paper-based ELISA revealed a high LOD (10 ng/mL) and a slight color difference between 10 ng/mL and 100 ng/mL, probably because the extra enzymes were trapped in the pores and hardly washed off (Fig. 5b). Compared to published results of other developed ELISA sensors for CAP, the nanofibrous membrane-based ELISA has the advantages at the sensitivity of naked eye distinction (Table 1). Thus, the use of the nanofibrous membranes with ultrahigh surface area indeed intensified colorimetric signal of the ELISA and produced sensors for rapid and sensitive detection without employing any instruments.

3.5. Selectivity and the impact of interference

Antibiotics with similar structures to CAP, such as florfenicol (FF), thiamphenicol (TAP) and penicillin (PCN), may interfere with the high-sensitivity of the nanofibrous membrane-based ELISA, resulting in false positives. To test whether FF, TAP and PCN bind to the CC-activated nanofibrous membrane sensor with CAP antibodies, each antibiotic was tested at a concentration of 100 ng/mL alongside a control group that did not contain any antibiotics. CAP showed a dramatical color change, but the other three antibiotics presented unchanged colors to the control group (Fig. 6). The selectivity of the competitive ELISA usually is described by a cross-reactivity ratio (CR%) which is calculated by the ratio of 50% inhibition concentration (IC_{50}) between other antibiotics and CAP. Here, 100 ng/mL FF, TAP and PCN exhibited 92.85%, 97.31% and 100% color intensity of the control group respectively, but the IC_{50}

Fig. 5. Optical images and color intensities (Absorbance or R values) of conventional ELISA. a) 96 well plate-based ELISA; b) nitrocellulose-based ELISA. (For interpretation of the references to color in this figure legend, the reader is referred to the Web version of this article.)

Table 1

Comparison of lowest distinguishable CAP concentration among competitive ELISA sensors from literature.

Solid Substrate	Signal Amplifying	Lowest instrument distinguishable concentration (ng/mL)	Lowest naked-eye distinguishable concentration (ng/mL)	reference
96 well plates	NA	0.1	NA	Wesongah et al. (2007) [20]
96 well plates	Fluoro-immunoassays	0.05	NA	Shen et al. (2006) [21]
96 well plates	Biotin-Streptavidin Amplified	0.042	NA	Wang et al. (2010) [22]
96 well plates	Biotin-Streptavidin Amplified	0.10	NA	Muhammad et al. (2017) [23]
lateral flow assay	Colloidal Gold Particles	0.3	10	Byzova et al. (2010) [24]
96 well plates	Gold Nanoparticles	0.3	5	Wang (2016) [25]
Paper-based	NA	100	800	Duyen (2017) [26]
Lateral flow assay	Quantum Dots	0.016	0.625	Xie et al. (2019) [27]
Solution	Ion amplified GNP	1.9	9.4–31.3	Wu et al. (2019) [10]
Solution	DNAzyme-functionalized gold nanoprobe	0.00013	NA	Huang (2019) [11]
Solution	DNA amplified GNP	2.2	150	Wu et al. (2020) [12]
96 well plates	NA	0.1	10	This work
Nitrocellulose membranes	NA	1	10	This work
Nanofibrous membrane	NA	0.1	0.3	This work

Fig. 6. Sensitivity and practicality of the sensor. a) interferences of varied antibiotics; b) optical images and c) R values of the reference, wild-caught salmon, and spiked salmon samples.

of CAP was around 0.2 ng/mL, indicating that the CR% values of the sensor to other antibiotics were lower than 0.5%. Thus, the results suggest that the antibody is specific to the target antibiotic, CAP, with high selectivity.

As a test for practical applications, the CC nanofibrous membrane-based immunosensor were employed in testing CAP in spiked salmons (Fig. 6b and c). CAP solutions of 0 ng/mL and 100 ng/mL were used as references in the tests. A bright blue color was achieved on the 0 ng/mL treated membrane, while the 100 ng/mL treated membrane exhibited a white color. Three pieces of salmons were processed and extracted with the solvents described in the experimental section. The samples revealed bright color, indicating no CAP or a concentration lower than the detection limit of 0.1 ng/mL in the samples. The R value of the wild samples was 91.6 ± 4.1 , which was close to the membrane treated by 0 ng/mL of CAP (92.0 ± 4.6). Then, a known quantity of CAP was spiked into a wild salmon filtrate. The samples spiked with 0.1 ng/mL CAP revealed a bright blue color (no significant color change from the reference), but the samples spiked with 0.3 ng/mL and 0.5 ng/mL exhibited white color close to the membrane treated by 100 ng/mL CAP, and the color difference is distinguishable by naked eyes. The R values of the spiked salmon samples were 100.1 ± 3.5 , 145.0 ± 1.8 and 155.9 ± 2.4 , respectively, which were close to R values of these concentrated CAP in PBS buffer (Fig. 3a). The salmon spiked with 0.1 ng/mL CAP showed the existence of 0.097 ng/mL with a recovery of 96.7% and standard deviation at 6.09% ($n = 3$); and the sample spiked with 0.3 ng/mL of CAP revealed 0.29 ng/mL with a recovery at 96.3% and standard deviation at 4.5% ($n = 3$). Since 0.5 ng/mL of CAP is

beyond the calibration range (Fig. 4) and the sensor revealed a white color without much difference from the 100 ng/mL reference, the recovery of CAP at 0.5 ng/mL could not be calculated.

4. Conclusions

We have developed a highly sensitive and naked-eye distinguishable immunoassay biosensor using microporous nanofibrous membranes as supported ELISA media. Electrospun PVA-co-PE nanofibrous membranes were chemically modified by cyanuric chloride (CC), glutaraldehyde (GA), and N, N'-disuccinimidyl carbonate (DSC). The CC treated membranes showed high sensitivity and stable colorimetric signal as a sensor media. Compared to the conventional ELISA, the ultrahigh surface area of the nanofibrous membranes and abundant reactive sites on surfaces of the nanofibers significantly increased antibody immobilization, enhanced colorimetric signal, and improved sensitivity of the membrane-based sensors. The sensor also demonstrated a desired selectivity to the target antibiotic. The sensor could accurately quantitatively measure CAP in spiked salmon samples and detected a trace amount of CAP in the samples.

CRedit authorship contribution statement

> Cunyi Zhao: Writing - original draft. Yang Si: Methodology. Bofeng Pan: Methodology. Ameer Y. Taha: Methodology. Tingrui Pan: Methodology. Gang Sun: Writing - review & editing.

Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgements

This work was supported by National Institute of Food and Agriculture, Department of Agriculture, United States (USDA-NIFA) grant #2018-67017-28116 and National Institute of Environmental Health Services (NIEHS), United States, Grant # 5P42ES004699-30 (University of California, Davis Superfund).

References

- [1] W. Witte, Medical Consequences of Antibiotic Use in Agriculture, American Association for the Advancement of Science, 1998.
- [2] M. Lipsitch, R.S. Singer, B.R. Levin, Antibiotics in agriculture: when is it time to close the barn door? *Proc. Natl. Acad. Sci. Unit. States Am.* 99 (9) (2002) 5752–5754.
- [3] Q. Chang, W. Wang, G. Regev-Yochay, M. Lipsitch, W.P. Hanage, Antibiotics in agriculture and the risk to human health: how worried should we be? *Evol. Appl.* 8 (3) (2015) 240–247.
- [4] G.G. Khachatourians, Agricultural use of antibiotics and the evolution and transfer of antibiotic-resistant bacteria, *Can. Med. Assoc. J.* 159 (9) (1998) 1129–1136.
- [5] CDC, <https://www.cdc.gov/drugresistance/index.html>.
- [6] N. Mungroo, S. Neethirajan, Biosensors for the detection of antibiotics in poultry industry—a review, *Biosensors* 4 (4) (2014) 472–493.
- [7] K. Kümmerer, Antibiotics in the aquatic environment—a review—part II, *Chemosphere* 75 (4) (2009) 435–441.
- [8] R. Hirsch, T.A. Ternes, K. Haberer, A. Mehlich, F. Ballwanz, K.-L. Kratz, Determination of antibiotics in different water compartments via liquid chromatography–electrospray tandem mass spectrometry, *J. Chromatogr. A* 815 (2) (1998) 213–223.
- [9] M.Y. Haller, S.R. Müller, C.S. McArdell, A.C. Alder, M.J. Suter, Quantification of veterinary antibiotics (sulfonamides and trimethoprim) in animal manure by liquid chromatography–mass spectrometry, *J. Chromatogr. A* 952 (1–2) (2002) 111–120.
- [10] Y.-y. Wu, B.-w. Liu, P. Huang, F.-Y.J. Wu, A novel colorimetric aptasensor for detection of chloramphenicol based on lanthanum ion-assisted gold nanoparticle aggregation and smartphone imaging, *Anal. Bioanal. Chem.* 411 (28) (2019) 7511–7518.
- [11] W. Huang, H. Zhang, G. Lai, S. Liu, B. Li, A. Yu, Sensitive and rapid aptasensing of chloramphenicol by colorimetric signal transduction with a DNzyme-functionalized gold nanoprobe, *Food Chem.* 270 (2019) 287–292.
- [12] Y.-Y. Wu, P. Huang, F.-Y. Wu, A label-free colorimetric aptasensor based on controllable aggregation of AuNPs for the detection of multiplex antibiotics, *Food Chem.* 304 (2020) 125377.
- [13] S. Liu, L. Dou, X. Yao, W. Zhang, B. Zhao, Z. Wang, Y. Ji, J. Sun, B. Xu, D. Zhang, Polydopamine nanospheres as high-affinity signal tag towards lateral flow immunoassay for sensitive furazolidone detection, *Food Chem.* (2020) 126310.
- [14] Y. Niu, P. Zhang, L. Wang, N. Li, Q. Lin, L. Liu, H. Liang, Z. Huang, X.J. Fu, Development of Double-Antibody Sandwich ELISA for Rapidly Quantitative Detection of Antigen Concentration in Inactivated SCRV Vaccine, *Aquaculture*, 2019, p. 734671.
- [15] L. Ji, C. Dong, R. Fan, S.J. Qi, A high affinity nanobody against endothelin receptor type B: a new approach to the treatment of melanoma, *Mol. Biol. Rep.* 47 (2020) 2137–2147.
- [16] Y. Si, Z. Zhang, W. Wu, Q. Fu, K. Huang, N. Nitin, B. Ding, G. Sun, Daylight-driven rechargeable antibacterial and antiviral nanofibrous membranes for bioprotective applications, *Sci. Adv.* 4 (3) (2018) eaar5931.
- [17] A.Y. El-Moghazy, C. Zhao, G. Istamboulie, N. Amaly, Y. Si, T. Noguer, G. Sun, Ultrasensitive label-free electrochemical immunosensor based on PVA-co-PE nanofibrous membrane for the detection of chloramphenicol residues in milk, *Biosens. Bioelectron.* 117 (2018) 838–844.
- [18] Z. Zhang, C.E. Richardson, M. Hennebel, A.Y. Taha, Validation of a one-step method for extracting fatty acids from salmon, chicken and beef samples, *J. Food Sci.* 82 (10) (2017) 2291–2297.
- [19] J. Zhu, G. Sun, Bio-functionalized nanofibrous membranes as a hybrid platform for selective antibody recognition and capturing, *RSC Adv.* 5 (36) (2015) 28115–28123.
- [20] J. Wesongah, G. Murilla, A. Guantai, C. Elliot, T. Fodey, A. Cannavan, A competitive enzyme-linked immunosorbent assay for determination of chloramphenicol, *J. Vet. Pharmacol. Therapeut.* 30 (1) (2007) 68–73.
- [21] J. Shen, Z. Zhang, Y. Yao, W. Shi, Y. Liu, S. Zhang, A monoclonal antibody-based time-resolved fluoroimmunoassay for chloramphenicol in shrimp and chicken muscle, *Anal. Chim. Acta* 575 (2) (2006) 262–266.
- [22] L. Wang, Y. Zhang, X. Gao, Z. Duan, S. Wang, Determination of chloramphenicol residues in milk by enzyme-linked immunosorbent assay: improvement by biotin–streptavidin-amplified system, *J. Agric. Food Chem.* 58 (6) (2010) 3265–3270.
- [23] M.I. Chughtai, U. Maqbool, M. Iqbal, M.S. Shah, T. Fodey, Development of in-house ELISA for detection of chloramphenicol in bovine milk with subsequent confirmatory analysis by LC-MS/MS, *J. Environ. Sci. Health B* 52 (12) (2017) 871–879.
- [24] N. Byzova, E. Zvereva, A. Zherdev, S. Eremin, B. Dzantiev, Rapid pretreatment-free immunochromatographic assay of chloramphenicol in milk, *Talanta* 81 (3) (2010) 843–848.
- [25] S. Wang, Z. Chen, J. Choo, L. Chen, Naked-eye sensitive ELISA-like assay based on gold-enhanced peroxidase-like immunogold activity, *Anal. Bioanal. Chem.* 408 (4) (2016) 1015–1022.
- [26] T.T.M. Duyen, H. Matsuura, K. Ujiie, M. Muraoka, K. Harada, K. Hirata, Paper-based colorimetric biosensor for antibiotics inhibiting bacterial protein synthesis, *J. Biosci. Bioeng.* 123 (1) (2017) 96–100.
- [27] S. Xie, K. Wen, S. Wang, J. Wang, T. Peng, G.M. Mari, J. Li, Z. Wang, X. Yu, H. Jiang, Quantitative and rapid detection of amantadine and chloramphenicol based on various quantum dots with the same excitations, *Anal. Bioanal. Chem.* 411 (10) (2019) 2131–2140.