Lawrence Berkeley National Laboratory

Recent Work

Title

THE CATALYTIC HYDRODESULFURIZATION OF THIOPHENE ON THE Mo(100) CRYSTAL SURFACE

Permalink

<https://escholarship.org/uc/item/90c2n9m4>

Authors

Gellman, A.J.
Farias, M.H.
Somorjai, G.A.

Publication Date

1984

Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

RECEIVED
LAWRENCE
BERKELEY LABORATORY

Materials & Molecular Research Division

APR 17 1984

LIBRARY AND
DOCUMENTS SECTION

Submitted to the Journal of Catalysis

THE CATALYTIC HYDRODESULFURIZATION OF THIOPHENE
ON THE Mo(100) CRYSTAL SURFACE

A.J. Gellman, M.H. Farias, and G.A. Somorjai

January 1984

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 6782.*

LBL-17144
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

THE CATALYTIC HYDRODESULFURIZATION OF THIOPHENE ON THE Mo(100) CRYSTAL SURFACE

A. J. Gellman, M. H. Farias, and G. A. Somorjai

Materials and Molecular Research Division
Lawrence Berkeley Laboratory and
Department of Chemistry
University of California
Berkeley, California 94720 USA

In this note we report that the catalytic hydrodesulfurization (HDS) of thiophene can be performed on the Mo(100) single crystal surface. The HDS of thiophene is often used to test the activity of supported molybdenum-sulfur catalysts and, in order to develop improved catalysts for this important process, a molecular level understanding of this reaction is desirable. To this end we are performing a surface science study of this system utilizing both UHV and high pressure techniques.

The experiments described here have been conducted in a UHV chamber equipped with a high pressure cell, described elsewhere. (1) Varying pressures of thiophene (1-5 torr) and hydrogen (100-800 torr) have been mixed and circulated through a loop attached to the cell. Products were analyzed by gas chromatography and reaction rates and product selectivities have been determined as functions of reactant pressures and crystal temperatures (250°C-420°C). In all cases the Mo crystal surface was determined to be initially clean by Auger Electron Spectroscopy (AES).

Over the range of experimental conditions employed the initial reaction rates have varied from .020 - .120 turnovers/site/sec assuming that each surface Mo atom is an active site. Final turnover numbers have been as high as 1500, indicating that the reaction is catalytic. The product distribution displayed in Table 1 is similar to that observed for a MoS₂ catalyst. (2) The thiophene pressure dependence appears to be low order or zero order. The hydrogen pressure dependence, displayed in Table 2, is however, more complicated and varies among the products. The temperature dependence of the rates, shown in Figure 1, also differs among the products and is similar to the temperature dependence of the product distribution

observed for the deoxygenation of tetrahydrofuran. (3) For our HDS reaction, butadiene is the only product showing Arrhenius-like temperature dependence having an activation energy of 14.4 kcal/mole.

The surface after the reaction is covered with sulfur and carbon. The sulfur coverage, in fact, appears to be in excess of one monolayer as determined by our AES calibration. (4) Furthermore, we have identified an ordered sulfur structure on the Mo surface. The LEED pattern of this structure, shown in Fig. 2, indicates a hexagonal overlayer, having a unit cell parameter of 2.7 Å, present on the square lattice of the Mo(100) substrate. In general this structure is difficult to produce and requires the annealing of the surface to a 700-800°C, after the reaction. On occasion, however, we have observed its presence immediately after the reaction without annealing of the surface. More importantly, in the cases in which we have started the reaction with this structure present on the surface it has remained unaltered, indicating that it is stable under reaction conditions. In these cases the initial activity is reduced to about half of the initially clean surface.

The HDS reaction over Mo(100) seems to be similar to that observed over the supported Mo/S catalysts. We are currently conducting detailed studies of the nature of the Mo single crystal surface present under reaction conditions and of the effects of surface composition on reaction rates and product distributions.

ACKNOWLEDGEMENTS: We would like to thank the Division of Material Sciences and Office of Basic Energy Sciences of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098, and the Exxon Research Corporation for support of this work.

TABLE 1. Product distribution of the HDS of Thiophene ($C_4H_4S = 2.7t$, $H_2 = 780t$, $T=340^\circ C$).

Butadiene	5.6%
1-butene	52.8%
trans-2-butene	19.4%
cis-2-butene	13.9%
n-butane	8.1%

TABLE 2. H_2 pressure dependence of HDS product rates of appearance. ($C_4H_4S=2.7t$, $T=340^\circ$). $r=A \times (PH_2)^n$

<u>Product</u>	<u>n</u>
butadiene	-0.18
1-butene	0.54
trans-2-butene	0.68
cis-2-butene	0.58
n-butane	1.10

FIGURES

- Figure 1. Arrhenius plot of the temperature dependence of the product appearance rates for the HDS of thiophene. ($C_4H_4S = 2.5t$, $H_2 = 780t$). The activation energy for the production of butadiene is $E_a = 14.4$ kcal/mole.
- Figure 2. LEED patterns of the hexagonal sulfur structure taken at normal and off-normal angles of incidence. The diffraction spots due to the Mo(100) form a square lattice. The hexagonal lattice causes the superimposed rings having twelve intensity maxima about the circumference.

REFERENCES

1. Farias, M.H., Gellman, A. J., Somorjai, G. A., submitted to Surface Science.
2. Kolboe, S., Canadian J. of Chem., 47, 352(1969).
3. Furminsky, E., Ind. Eng. Chem. Prod. Res. Dev., 22, 31(1983).
4. Salmeron, M., Somorjai, G. A., Chianelli, R. R., 127, 526(1983).

XBL 839-11386

Fig. 1

XBB 838-7091

Fig. 2

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720