Lawrence Berkeley National Laboratory

Recent Work

Title

Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench: II. High-strength, laminated Ag-sheathed Bi-2223 tapes

Permalink

<https://escholarship.org/uc/item/93b35208>

Journal

Superconductor Science and Technology, 31(1)

ISSN

0953-2048

Authors

Shen, T
Ye, L
Higley, H

Publication Date

2018

DOI

10.1088/1361-6668/aa976c

Peer reviewed

PAPER

Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench: II. High-strength, laminated Ag-sheathed Bi-2223 tapes

To cite this article: Tengming Shen *et al* 2018 *Supercond. Sci. Technol.* **31** 015012

View the [article online](#) for updates and enhancements.

Related content

- [Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench. I. Ag/Bi2Sr2CaCu2Ox multifilament round wires](#)
Liyang Ye, Pei Li, Jan Jaroszynski *et al.*
- [Quench degradation limit of multifilamentary Ag/Bi2Sr2CaCu2Ox round wires](#)
Liyang Ye, Pei Li, Tengming Shen *et al.*
- [High-field quench behavior and dependence of hot spot temperature on quench detection voltage threshold in a Bi2Sr2CaCu2Ox coil](#)
Tengming Shen, Liyang Ye, Daniele Turroni *et al.*

Recent citations

- [Impact of Fatigue Loading on the Critical Current of Bi-2223 Tapes under Background Magnetic Field](#)
Wei Chen *et al*

IOP | ebooks™

Bringing you innovative digital publishing with leading voices to create your essential collection of books in STEM research.

Start exploring the collection - download the first chapter of every title for free.

Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench: II. High-strength, laminated Ag-sheathed Bi-2223 tapes

Tengming Shen^{ID}, Liyang Ye¹ and Hugh Higley

Lawrence Berkeley National Laboratory, Berkeley, CA 94720, United States of America

E-mail: tshen@lbl.gov

Received 11 August 2017, revised 11 October 2017

Accepted for publication 1 November 2017

Published 29 November 2017

Abstract

In article I of this series, we described a spiral coil quench technique for probing the influence of the superconductor stress and strain state during normal operation on its margin to degradation during a quench and applied to a Bi-2212 round wire. Here we extend this technique to study the failure mechanisms and limits of high-strength Bi-2223 tapes experiencing a quench while carrying a large current in a high magnetic field. In contrast to Bi-2212 magnets made via a wind-and-react technique for which bending strains can be ignored, Bi-2223 magnets are made with a react-and-wind technique for which bending strain is significant. The critical tensile stress of Bi-2223 tapes (type HT-NX) decreases from >440 MPa for straight samples to 185 MPa after being bent to a diameter D of 50 mm. For HT-NX tapes with $D = 50$ mm, the quench degradation limit, measured using maximum allowable temperature during a quench $T_{\text{allowable}}$, is greater than 300 K for axial tensile stress $\sigma_a < 94$ MPa; it decreases with increasing tensile axial stress σ_a nonlinearly, dropping to 230 K for $\sigma_a = 125$ MPa. $T_{\text{allowable}}(\sigma_a)$ experimental data at $D = 50$ mm is consistently predicted by a general strain model that assumes that quench degradation in NX/Bi-2223 is driven by axial tensile strain in Bi-2223 filaments exceeding the irreversible strain limit. The $T_{\text{allowable}}(\sigma_a)$ is then predicted for various D including $D = 80$ mm important for NMR magnets. The given $T_{\text{allowable}}(D, \sigma_a)$ is easy to use and important for finding the balance between operation stress, and therefore magnetic field generation efficiency, and operation margin when designing a superconducting magnet using Bi-2223 tapes.

Keywords: Bi-2223, superconducting magnet, quench protection, strain properties of superconductors

(Some figures may appear in colour only in the online journal)

Introduction

Despite being brittle, several superconductors, including Nb₃Sn, Bi-2212, Bi-2223, REBCO, and MgB₂, have been arduously developed into the practical form of metal/superconductor composite wire or tape and found or been finding

applications in superconducting magnets. Superconductors within high-field magnets must withstand high stresses and a variety of strains resulted from fabrication and operation, which include bending strain due to coil winding, strain due to operational electromagnetic stresses, and thermal strain caused by differential thermal expansion between the metal matrix and superconductors during a quench. Determining the true practical conductor limit of superconductors requires

¹ Now with GE Healthcare.

taking all of these strains into consideration. Although the mechanical properties of superconductors and the dependence of their critical current density on strains have been studied extensively [1–4], measurements conducted so far evaluate only one or more but not all of these strains seen by superconductors within a magnet. For example, the tensile stress-strain- I_c test using straight samples [1–3] and the I_c -strain tests using hairspring rigs [5, 6] ignore bending strain and thermal strain due to a quench, whereas bending tests do not consider strain due to Lorentz force and thermal strain due to a quench [4]. It is understandable that thermal strain due to a quench is rarely considered [7–9] because the failure mechanisms of a superconductor during a quench have yet to be determined.

We developed a spiral coil quench technique capable of evaluating all these strains within a test [10]. We have applied it to Bi-2212 round wire, which is made into magnets using a wind-and-react technique that features zero winding strain, to probe the influence of the operational stress and strain state on its margin to degradation during a quench. We found that quench induced degradation for Bi-2212 round wires is driven by axial tensile strain and that the dependence of the margin to degradation during a quench on the operational electromagnetic stresses can be predicted.

Here we extend this technique to study failure mechanisms and limits of high-strength, high-current Bi-2223 tapes, which is made into magnets using a react-and-wind technique that features a large bending strain. The Ag/Bi-2223 tape was the first high- T_c cuprate conductor fabricated into km length conductor with the capability to carry high supercurrent, benefiting from the rather simple powder-in-tube fabrication and the invention of the overpressure processing. However, the application of Bi-2223 tapes to high-field magnets had been hampered by low tensile strength due to the necessary use of silver as the matrix. The strength of Ag/Bi-2223 tapes has been improved by laminating them with Cu-alloy or stainless steel tapes. Potential applications of these high-strength, laminated Bi-2223 tapes, with MRI, high-field NMR [11], and research superconducting magnets have recently been explored and demonstrated in a 25 T cryogen-free superconducting magnet which includes an 11 T Bi-2223 insert [12], a 20 K, 3 T MRI magnet [13, 14], a 1020 MHz NMR magnet with a 3.6 T Bi-2223 insert coil in series with 20.4 T Nb-Ti and Nb₃Sn outsert coils [15], and a 28 T solenoid [16] [17]. Recently, ultra-high-strength, Bi-2223 tapes ('DI-BSCCOTM' type HT-NX) have become available from Sumitomo Electric Industries (SEI). The tape, laminated with pretensioned Ni-Cr alloy, has a critical tensile strength of greater than 500 MPa at 77 K [18], increasing from about 130 MPa for the type H and type HT conductors that have no mechanical reinforcements [18], and from ~250 MPa for type HT-CA (Cu-alloy laminated) and type HT-SS (stainless steel laminated) conductors [1]. Its critical tensile strain, about 0.55% at 77 K, is also significantly higher than those of the type H and type HT conductors (~0.2%) and type HT-CA

and type HT-SS conductors (~0.4%) [1]. Our experiments and analysis are conducted on the type HT-NX tapes.

Methods

Sample preparation and critical current measurement

Samples are commercial ultra-high-strength, Bi-2223 tapes ('DI-BSCCOTM' type HT-NX) available from SEI and fabricated using controlled-overpressure processing. The tape has an average thickness of 0.31 mm and a width of 4.5 mm. It is a three-ply tape with two Ni-Cr alloy tapes (thickness = 30 μ m each) soldered to two sides of a type HT Ag/Bi-2223 tape. The temperature and field dependence of its sister wires ('DI-BSCCOTM' type H and type HT) $I_c(B, T)$ is given at http://global-sei.com/super/hts_e/type_ht.html and by Wimbush *et al* [19]. Its critical bending diameter is around 30 mm (95% I_c retention) [20]. Its modulus at 77 K is 90 GPa and its irreversible tensile axial strain is estimated to be 0.55%, measured by tensile stress measurements.

A 1 m of such tape was wound on a G-10 barrel with spiral grooves (50 mm diameter, 5.6 mm pitch length) (figure 1(a)). The barrel design is similar to those used for measuring the critical current (I_c) of ITER Nb-Ti and ITER Nb₃Sn strands [21]. The critical current was determined using a standard four-point resistive measurement technique with an electric field criterion of 1 μ V cm⁻¹ at 4.2 K and in magnetic fields up to 15 T. The magnetic field was applied parallel to the central axis of the barrel and thus parallel to the tape. During I_c measurements, the transport current is configured such that the Lorentz force pushes the tape against and is thus supported by the G-10 barrel and experiences zero hoop stress (figure 1(b)).

Determining the critical axial tensile stress using hoop stress

The critical axial stress at which I_c degrades irreversibly is an important engineering parameter and was determined using the spiral coil as follows. The spiral coil technique allows a hoop stress induced using a transport current oriented such that the Lorentz force was outward away from the G-10 barrel ($\sigma_h = BJr$, where J is the current density averaged over the entire wire cross-section and r the radius of the spiral; see figure 1(c)). The transport critical current was re-measured after applying the hoop stress.

Quench behaviors investigation

The coil was also instrumented with a heater for inducing a quench, and voltage taps and thermocouples for monitoring quench propagation (figures 2(a) and (c)). The heater is an epoxy spot heater (Ecobond 60 L) designed for triggering small normal zones and also easy to mount onto the sample. The normal zone evolution was monitored via thermocouples (E-type, AWG32) and voltage taps around the hot zone. The

Figure 1. (a) A photo of a Bi-2223 spiral coil mounted on a G-10 barrel, (b) illustration of the safe mode for I_c measurement, (c) illustration of the hoop stress mode for investigating conductor limits.

hot spot temperature was obtained by cross-examining the measured resistivity of the hot zone with the temperature dependence of Bi-2223 wire resistivity and verified by thermocouples. A typical sequence of voltage signal development after a quench is shown in figure 2(b).

Figure 2. (a) Schematics of instrumentation used for the heater-induced quench experiment (for $V_0, V_{L1}, V_{L2}, V_{L3}, V_{R1}, V_{R2}, V_{R3}$, tap lengths are 1 cm.), (b) typical $V(t)$ during a quench of Bi-2223 HT-NX tape, (c) a photo of a Bi-2223 spiral coil, instrumented with voltage taps (VT = voltage tap) and thermocouples, mounted on the test probe. TC = thermocouple; VT = voltage tap.

Determining the maximum allowable temperature during a quench, $T_{allowable}$, with increasing axial stress

Spiral coil geometry lends itself well to simulating a quench with a large current in high magnetic field and thus large Lorentz forces. This is accomplished by applying a controlled hoop stress and initiating a quench using a heater, similarly to previous studies on short straight samples and coils. Samples were quenched with raising hot spot temperature incrementally, beginning around 50 K, and after each quench, the I_c of the sample was re-measured with zero hoop stress. The safety margin was measured using the maximum allowable hot spot temperature $T_{allowable}$ during a quench, which is defined as the hot spot temperature at which I_c of the wire degrades by 5%. This experiment is representative of quenches in high-field magnets.

Figure 3. $I_c(B)$ and n -value of the Bi-2223 tapes at 4.2 K in ascending and descending magnetic field.

Results

$I_c(B)$ and n -value

Figure 3 presents $I_c(B)$ and n -values of two barrel samples, confirming high I_c and n -values of this material for practical magnet applications. Samples show high strong hysteresis in I_c , with I_c measured at decreasing field being significantly higher than I_c measured at ascending field.

Axial tensile stress limit for $D = 50$ mm

Figure 4 presents I_c with increasing axial stress for a barrel with $D = 50$ mm. I_c shows irreversible degradation ($I_c(\text{after stress})/\text{initial } I_c \leq 0.99$) with axial stress greater than 150 MPa, and at 185 MPa, loses 5% of its original I_c . The axial stress limit found is significantly lower than the values measured from tensile tests of straight samples.

Figure 4. I_c at 4.2 K and 15 T for HT-NX Bi-2223 tapes ($D = 50$ mm) with increasing Lorentz force applied. I_c was measured without hoop stresses after each force cycle.

Stress dependence of maximum allowable temperature during a quench $T_{\text{allowable}}(\sigma_a)$ for $D = 50$ mm

Figure 5 presents the results of quench experiments with or without (safe mode) hoop stress at 4.2 K and 15 T. Without hoop stress and with hoop stress smaller than 94 MPa, samples survive a hot spot temperature greater than 300 K (Q5, sample #1) whereas under hoop stress of 121 MPa, the maximum allowable temperature during a quench, $T_{\text{allowable}}$, decreases to 232 K. Figure 6 presents $T_{\text{allowable}}$ as a function of applied stress, showing the clear trend of the decrease of $T_{\text{allowable}}$ with increasing axial stress.

Quench induced degradation behaviors

Figure 7 presents a typical quench degradation behavior. The degradation rather localized due to slow normal zone propagation. Similar to Bi-2212, the degradation correlates with the local hot spot temperature T_{max} well.

Analysis and discussion

Failure analysis

In composite superconducting wires the total axial strain of superconductor filaments in a composite superconductors, ϵ_t , during a quench can be described as

$$\epsilon_t = \epsilon_b + \epsilon_L + \epsilon_q \quad (1)$$

where ϵ_b is the bending strain, ϵ_L the strain due to Lorentz forces, and ϵ_q the axial tensile strain from differential thermal expansion between the entire wire and the superconductor filaments due to the temperature rise during the quench. For this experiment, $\epsilon_b = 0.32\%$ for $D = 50$ mm (given by $\epsilon_b = \frac{2 \cdot t}{D}$, where t is the distance of the outermost Bi-2223 filaments away from the central bending plane; here $t = 0.08$ mm), and $\epsilon_L = \epsilon_h$, which is the hoop strain (given by $\epsilon_h = \frac{\sigma_h}{E}$, where E is

Figure 5. Record of I_c and maximum hot spot temperature T_{max} for quench experiments performed on (a) sample #1, and (b) sample #2.

the modulus of HT-NX Bi-2223. Here $E = 90$ GPa). Assuming that ϵ_q relates to T_{max} only and does not relate to either temperature rise rate dT_{max}/dt or temperature gradient dT_{max}/dx , ϵ_q in the Bi-2223 filaments can be appropriated by

$$\epsilon_q|_{\text{Bi-2223 filaments}} = \frac{\Delta L}{L_{T_{max}-4.2\text{ K}}|_{\text{wire}}} - \frac{\Delta L}{L_{T_{max}-4.2\text{ K}}} \times |_{\text{Bi-2223 filaments}} \quad (2)$$

where $\Delta L/L_{T_{max}-4.2\text{ K}}|_{\text{Bi-2223 HT-NX tape}}$ and $\Delta L/L_{T_{max}-4.2\text{ K}}|_{\text{Bi-2223 filaments}}$ the total linear expansion from 4.2 K to T_{max} for the entire wire and the Bi-2223 filaments, respectively. As a reference, $\Delta L/L_{300\text{ K}-4.2\text{ K}}|_{\text{wire}} = 0.31\%$ whereas $\Delta L/L_{300\text{ K}-4.2\text{ K}}|_{\text{Bi-2223 filaments}} = 0.16\%$ [22].

Figure 8 plots the total axial strain applied to the Bi-2223 filaments, including ϵ_h and ϵ_q for cases A–E in figure 4. The failure limits shown are remarkably consistent among all cases: at a total axial strain of 0.52%–0.55%, I_c of Bi-2223 conductors degrades irreversibly.

The implications of figure 8 are strong. First, it shows that the failure during a quench for Bi-2223 conductor is

Figure 6. Maximum allowable temperature $T_{allowable}$ during a quench as a function of hoop stress σ_h applied for HT-NX Bi-2223 tape ($D = 50$ mm).

Figure 7 An example of quench induced I_c distribution and associated hot spot temperature distribution after a quench (Q17 for sample #1).

driven by axial tensile strain in Bi-2223 filaments and occurs when their axial strain exceeds the measured irreversible tensile strain limit. Second, both bending strain and quench induced thermal strain manifest themselves as axial strains that can be simply be added into the total axial strain. Therefore, it is rather simple to predict the failure limits of Bi-2223 conductors, including the type H, type HT, type HT-SS, type HT-CA, and type HT-NX during a quench.

Failure limit prediction

Based on these new findings, figure 9 predicts the failure limits of Bi-2223 as a function of bending diameter D when there is no quench ($\sigma_c = E \cdot \epsilon'_c = E \cdot (\epsilon_c - \epsilon_b)$, where ϵ'_c is the modified irreversible tensile axial strain with bending strain $\epsilon_b = \frac{2 \cdot t}{D}$ taken into consideration). Critical tensile stress σ_c decreases with bending diameter D , dropping to ~ 300 MPa with $D = 80$ mm, and ~ 200 MPa with $D = 50$ mm. The prediction is consistent with this experiment and $\sigma_c = 400$ MPa at $D = 108$ mm found by Miyoshi *et al* [23].

Figure 8. Strain seen by the Bi-2223 filaments for quenches and non-quench scenario presented in figure 4.

Figure 9. Predicted critical tensile stress as a function of bending diameter D for Bi-2223 HT-NX.

Figure 10. Maximum allowable temperature $T_{\text{allowable}}$ during a quench as a function of hoop stress σ_h applied for HT-NX Bi-2223 tape with various bending diameters.

Figure 10 predicts the failure limits of Bi-2223 as a function of bending diameter D when there is a quench, expressed as $T_{\text{allowable}}(D, \sigma_a)$ ($\sigma_a = \sigma_h$ in this case). This plot has important engineering values because it defines the practical limits of Bi-2223 conductors. At $D = 80$ mm which is required by NMR magnets, to keep $T_{\text{allowable}} > 300$ K, the hoop stress applied should not exceed 200 MPa. From this plot, it is clear that the design of this 25 T magnet [8, 12] ($D = 95.8$ mm, $\sigma_h = 323$ MPa; $T_{\text{allowable}} = 200$ K according to figure 10) is too aggressive, as it likely fails during quenches if the maximum temperature during a quench exceeds 200 K. The plot is easy to use as $T_{\text{allowable}}$ can be correlated to current density in Ag matrix J_m , and quench protection parameters including t_s , the time between a quench occurring and the magnet current decaying, and t_D , the time constant of magnet current decay through a simple adiabatic heat transfer analysis.

Our $T_{\text{allowable}}(D, \sigma_a)$ predication is a conservative limit for using Bi-2223 type HT-NX conductor for several reasons. σ_h decreases, increasing $T_{\text{allowable}}$, if a quench is detected and magnet current is forced to decay. Moreover, in a solenoid, the highest hoop stress is not necessarily at the innermost layer, where the bending strain is most significant and the field is strongest.

Other failure mechanisms

One of the samples also failed with N-Cr-alloy buckling due to a quench and delaminating from Ag/Bi-2223 tape. These additional failure mechanisms are likely a characteristics shared by all laminated Bi-2223 conductors.

Conclusions

We extend a new spiral coil quench technique to explore the practical engineering limits of an ultra-high-strength, high-current Bi-2223 tape. Our experiments show that the failures of Bi-2223, like Bi-2212 wires, during a quench are driven by axial tensile strain. Our analysis shows that the experimental results can be predicted using a simple strain analysis. We further extended the analysis to predict the maximum allowable temperature during a quench $T_{\text{allowable}}(D, \sigma_a)$ at various bending diameters. The conductor degrades permanently above $T_{\text{allowable}}$. The resulted plot is easy to use and has significant engineering values for designing magnets using Bi-2223 conductors.

Acknowledgments

This work was funded by the Office of High Energy Physics of the US Department of Energy (DOE) through a US DOE Early Career Award. Work at Lawrence Berkeley National Lab was supported by the Director, Office of Science, Office of High Energy Physics, of the US Department of Energy under Contract No. DE-AC02-05CH11231. We thank Arno Godeke and Scott Marshall with the National High Magnetic

Field Laboratory for supplying conductors used in this study.

ORCID iDs

Tengming Shen <https://orcid.org/0000-0003-1581-320X>

References

- [1] Ayai N *et al* 2009 Electrical and mechanical properties of DI-BSCCO type HT reinforced with metallic sheathes *IEEE Trans. Appl. Supercond.* **19** 3014–7
- [2] Sugano M, Osamura K and Hojo M 2003 Mechanical properties of Bi2223 filaments extracted from multifilamentary tape evaluated by the single-fibre tensile test *Supercond. Sci. Technol.* **16** 571
- [3] Sunwong P, Higgins J S and Hampshire D P 2011 Angular, temperature, and strain dependencies of the critical current of DI-BSCCO tapes in high magnetic fields *IEEE Trans. Appl. Supercond.* **21** 2840–4
- [4] Shin H-S and Katagiri K 2003 Critical current degradation behaviour in Bi-2223 superconducting tapes under bending and torsion strains *Supercond. Sci. Technol.* **16** 1012
- [5] Kitaguchi H, Itoh K, Kumakura H, Takeuchi T, Togano K and Wada H 2001 Strain effect in Bi-based oxide/Ag superconducting tapes *IEEE Trans. Appl. Supercond.* **11** 3058–61
- [6] ten Haken B, Beuink A and ten Kate H H 1997 Small and repetitive axial strain reducing the critical current in BSCCO/Ag superconductors *IEEE Trans. Appl. Supercond.* **7** 2034–7
- [7] Hahn S, Bascunán J, Yao W and Iwasa Y 2010 Two HTS options for a 600 MHz insert of a 1.3 GHz LTS/HTS NMR magnet: YBCO and BSCCO *Physica C* **470** 1721–6
- [8] Hanai S, Tsuchihashi T, Ioka S, Watanabe K, Awaji S and Oguro H 2017 Development of an 11 T BSCCO insert coil for a 25 T cryogen-free superconducting magnet *IEEE Trans. Appl. Supercond.* **27** 4602406
- [9] Yanagisawa Y *et al* 2015 Combination of high hoop stress tolerance and a small screening current-induced field for an advanced Bi-2223 conductor coil at 4.2 K in an external field *Supercond. Sci. Technol.* **28** 125005
- [10] Ye L, Li P, Jaroszynski J, Schwartz J and Shen T 2016 Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench: I. Ag/Bi₂Sr₂CaCu₂O_x multifilament round wires *Supercond. Sci. Technol.* **30** 025005
- [11] Marshall W, Bird M, Godeke A, Larbalestier D, Markiewicz W and White J 2017 Bi-2223 test coils for high-resolution NMR magnets *IEEE Trans. Appl. Supercond.* **27** 4300905
- [12] Awaji S *et al* 2017 First performance test of a 25 T cryogen-free superconducting magnet *Supercond. Sci. Technol.* **30** 065001
- [13] Terao Y *et al* 2013 Newly designed 3 T MRI magnet wound with Bi-2223 tape conductors *IEEE Trans. Appl. Supercond.* **23** 4400904
- [14] Kitaguchi H *et al* 2010 Development of a Bi-2223 HTS magnet for 3T MRI system for human brains *IEEE Trans. Appl. Supercond.* **20** 710–3
- [15] Hashi K *et al* 2015 Achievement of 1020 MHz NMR *J. Magn. Reson.* **256** 30–3
- [16] Kajita K *et al* 2016 Degradation of a REBCO Coil due to cleavage and peeling originating from an electromagnetic force *IEEE Trans. Appl. Supercond.* **26** 1–6
- [17] Maeda H *et al* 2016 Development of super-high-field NMR operated beyond 1 GHz using high-temperature superconducting coils *eMagRes* **5** 1109
- [18] Godeke A *et al* 2016 A feasibility study of high-strength Bi-2223 conductor for high-field solenoids *Supercond. Sci. Technol.* **30** 035011
- [19] Wimbush S C, Strickland N M and Long N J 2015 Low-temperature scaling of the critical current in 1 G HTS Wires *IEEE Trans. Appl. Supercond.* **25** 1–5
- [20] Nakashima T *et al* 2015 Drastic improvement in mechanical properties of DI-BSCCO wire with novel lamination material *IEEE Trans. Appl. Supercond.* **25** 1–5
- [21] Pong I *et al* 2012 Worldwide benchmarking of ITER internal tin and NbTi strands test facilities *IEEE Trans. Appl. Supercond.* **22** 4802606
- [22] Ekin J 2006 *Experimental Techniques for Low-Temperature Measurements: Cryostat Design, Material Properties and Superconductor Critical-Current Testing* (Oxford: Oxford University Press)
- [23] Miyoshi Y, Nishijima G, Kitaguchi H and Chaud X 2015 Hoop stress test on new high strength alloy laminated Bi-2223 conductor *Supercond. Sci. and Technol.* **28** 075013