

Lawrence Berkeley National Laboratory

Recent Work

Title

Bulk and surface characterization of a dewetting thin film polymer bilayer

Permalink

<https://escholarship.org/uc/item/97h6z2z8>

Journal

Applied Physics Letters, 73(25)

Author

Ade, H.

Publication Date

1998-06-23



ERNEST ORLANDO LAWRENCE BERKELEY NATIONAL LABORATORY


Bulk and Surface Characterization of a Dewetting Thin Film Polymer Bilayer

H. Ade, D.A. Winesett, A.P. Smith, S. Anders,
T. Stammeler, C. Heske, D. Slep, M.H. Rafailovich,
J. Sokolov, and J. Stöhr

Advanced Light Source Division

June 1998

Submitted to
Applied Physics Letters



REFERENCE COPY	Copy 1
Does Not Circulate	
Bldg. 50 Library - Ref.	
Lawrence Berkeley National Laboratory	

LBNL-41990

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

Bulk and Surface Characterization of a Dewetting Thin Film Polymer Bilayer

H. Ade, D.A. Winesett, A.P. Smith, S. Anders, T. Stammner, C. Heske,
D. Slep, M.H. Rafailovich, J. Sokolov, and J. Stöhr

Advanced Light Source Division
Ernest Orlando Lawrence Berkeley National Laboratory
University of California
Berkeley, California 94720

June 1998

This work was supported by the Director, Office of Energy Research, Office of Biological and Environmental Research, under Contract Nos. DE-FG02-89ER60858 and DE-FG02-93ER45481, and by the National Science Foundation under Grant Nos. DBI-9605045 (Lucent Technologies Bell Labs), ECS-9510499, DMR-9458060, and DMR-9732230, through the U.S. Department of Energy Contract No. DE-AC03-76SF00098 at the Lawrence Berkeley National Laboratory.

Light Source Note:	
Author(s) Initials	SA. 6/23/98
Group Leader's Initials	MP 6/23/98
Date	Date

Bulk and surface characterization of a dewetting thin film polymer bilayer

H. Ade^{a)}, D. A. Winesett, and A. P. Smith

Dept. of Physics, North Carolina State University, Raleigh, NC 27695-8202

S. Anders, T. Stammer, and C. Heske,

Advanced Light Source, Ernest Orlando Lawrence Berkeley National Laboratory, Berkeley, CA94720

D. Slep

Advanced Development and Research, Hilord Chemical Corp., Hauppauge, NY11788

M. H. Rafailovich and J. Sokolov

Dept. Materials Science and Engineering, SUNY@Stony Brook, Stony Brook, NY11794

J. Stöhr

IBM Research Division, Almaden Research Center, 650 Harry Road, San Jose, CA95120

^{a)} Corresponding author. E-mail: harald_ade@ncsu.edu.

We have monitored the progression of the dewetting of a partially brominated polystyrene (PBrS) thin film on top of a polystyrene (PS) thin film with Scanning Transmission X-ray Microscopy (STXM) as well as PhotoEmission Electron Microscopy (PEEM). Both STXM and PEEM utilize Near Edge X-ray Absorption Fine Structure (NEXAFS) spectroscopy to quantitate the composition at high spatial resolution. We mapped the projected thickness of each constituent polymer species and the total thickness of the film with STXM, while we determined the surface composition with PEEM. Our data show that the PBrS top layer becomes encapsulated during the later stages of dewetting and that AFM topographs can not be utilized to determine the contact angle between PBrS and PS.

Thin films of polymers have numerous technological applications ranging from multi-color photographic printing to paints, adhesives, index-matched optical coatings, photo-resists, and low dielectric electronic packaging. An understanding of dewetting and decomposition phenomena of blends and bilayers and their dynamics is important in order to have a better understanding of the use of polymers in these applications. In comparison to bulk properties, much less is known about the properties of polymers when they are processed into thin films. Typically, the polymer-substrate and polymer-air interfacial energies or kinetic barriers play important roles in determining the morphology and dynamics in thin films. A detailed understanding of thin film properties, such as composition and morphology, and possible deviations from bulk properties is highly desirable and numerous studies on blends¹⁻⁷ and bilayers^{8,9} have recently been undertaken. Most of these studies rely on Atomic Force Microscopy or other methods that can not always provide the sought after answers. In dewetting bilayers, for example, it is often the goal to determine the interfacial energy or the Flory parameter between the two polymers. The contact angle, which depends on the interfacial energies between the two polymers, can in principal be determined from the slope of AFM topographs⁸⁻¹⁰. However, this is a very indirect method since force or friction modulation contrast is only a reflection of the mechanical response of the sample and is not an unambiguous identification of chemical composition at the interface. Furthermore, if the polymers are in the liquid state then the Newman, rather than the Young's contact angle, must be determined⁹ which requires a precise knowledge of the curvature of the polymer/polymer interface. Hence, a 3-dimensional quantitative compositional analysis tool would be ideal to study morphologies in these films and dynamic phenomena such as phase separation and dewetting. We present here the combination of Near Edge X-ray Absorption Fine Structure (NEXAFS) imaging in transmission^{11,12} and surface sensitive modes^{13,14} as a new approach to characterize polymer thin films and investigated model thin films of blends and bilayers of polystyrene (PS) and brominated polystyrene (PBrS). The PS/PBrS system is difficult to study by other techniques. No mechanical or friction differences can be detected between the two polymers in scanning force microscopy and the Bromine content is insufficient to stain one of the phases in transmission electron microscopy. Our data provide important information about the 3-dimensional morphology of the systems investigated, and show that the PBrS gets encapsulated by PS in both blends and bilayers after annealing even in the case where the PBrS started out as the surface layer.

NEXAFS imaging of polymers has advantages over other forms of microscopy primarily because of its low damage^{11,15}, sufficient chemical sensitivity to distinguish essentially most, if not all, polymers^{16,17}, and the possibility for quantitative analysis¹⁸. Here we explore explicitly the advantages

of combining surface sensitive and bulk sensitive data acquisition modes of x-ray microscopy. We also demonstrate quantitative mapping of composition in thin synthetic polymer films with transmission NEXAFS microscopy, and discuss the implications for the 3-dimensional morphology of the systems investigated. We have utilized the Stony Brook Scanning Transmission X-ray Microscope (STXM)¹⁹ located at the National Synchrotron Light Source (NSLS) to measure the bulk composition of thin films as thick as 500 nm. STXM uses zone plates optics to form a micro-focus corresponding to a spatial resolution of approximately 50 nm. In order to assess the surface composition, we have utilized a Photoelectron Emission Microscope (PEEM) at beamline 8.0 at the Advanced Light Source in Berkeley. The electron optical column of the microscope is used to form an image of the emitted electrons. The microscope is a two-lens system operating at a nominal voltage of 10 kV, and is described in detail elsewhere²⁰. We investigated blend and bilayer samples of highly brominated polystyrene (79% degree of Bromination) and polystyrene (PS). The blends (50/50% by weight) were spun cast from toluene solution onto a native oxide covered Si substrate. The film thickness was monitored with multiple wavelength ellipsometry. The bilayers were prepared by spin casting the PS and PBrS separately onto silicon substrates and then floating the PBrS layer on top of the PS layer. The samples were annealed on the substrate under vacuum to initiate the dewetting in the bilayer or to further increase the phase separation in the blends. The samples investigated with PEEM were left on the Si substrate, while the samples investigated with STXM were transferred to a TEM grid. The blends investigated had a thickness of about 45 nm, while the bilayer were 30 nm of PBrS on top of 30 to 40 nm thick PS.

Homopolymer films were utilized to measure reference spectra as the basis for the quantitative NEXAFS analysis. The linear absorption coefficients of the two polymers are shown in Fig. 1. Regarding bulk compositional analysis, we show as an example the results from a 30nm/40nm PBrS/PS bilayer annealed for one week at 180°C. We acquired STXM images of the same sample area at four characteristic energies: 281.8 eV (pre-edge), 285.2 eV (π^* of PS, main π^* of PBrS), 286.5 eV (C-Br shifted π^* of PBrS), and 310 eV (post-edge). Each image contains information about the PS and PBrS composition and thickness, with the weight governed by the linear absorption coefficient of the two polymers (Fig. 1). While these absorption micrographs (not shown here) by themselves provide a qualitative understanding of the dewetting morphology and to some extent dynamics, actual sample thickness maps or quantitative composition maps can not be accurately determined from simple observation of these images. We have thus utilized a "singular value decomposition" procedure¹⁸ to calculate PS and PBrS equivalent thickness maps from the transmission images. This process makes use of the carefully measured absorption coefficients from the reference homopolymers (Fig. 1).

The quantitative PS, PBrS, and total thickness (sum of PS and PBrS) maps are shown in Figs. 2 (a), (b), and (c) respectively. From the figures, we can see the characteristic Voronoi tessellation dewetting patterns that form prior to droplet formation²¹. The respective line profile as indicated in the images is shown directly below each figure. From Fig. 2(a), we can see that a PS ridge surrounds the interconnecting strands of the PBrS layer. The PBrS core within the strands is seen in figure 2b to rise much more sharply. Consequently, it is clear that the contact angle between the PS and PBrS features can not be measured from the topographic features alone. Even though the dewetting process has not reached equilibrium yet, we estimate the contact angle from the cross sectional scan to be approx. 10° when measured from the PS and total density maps in figures 2a and 2c. This value is in agreement with that obtained from atomic force microscopy of the sample before removal from the substrate. The contact angle of the PBrS core on the other hand is approx. 20° which is closer to the calculated value of 28° based on measurements of the interfacial energy of the two polymers²².

In order to address the issue of encapsulation, we determined the surface composition of a similar sample, i.e. a 30nm/34 nm PBrS/PS bilayer annealed for 11 days. PEEM images acquired at 300 eV are presented in Fig. 3 and show Voronoi tessellation patterns²¹ similar to the ones observed in figure 2 with transmission NEXAFS. Contrast in PEEM is not only determined by composition, but also by topography and illumination. The sides of the spines and the spines themselves are dark due to topographic contrast that arises from the reduced collection efficiency in the PEEM from locations that are not perpendicular to the optical axis. In addition, the sample is illuminated at a shallow angle of about 30° and the local photon intensity of the sample depends on the topography. Partial or complete shadowing as well as increased emission can contribute to contrast in PEEM images. While the overall collection efficiency of the photoelectrons and the illumination contrast is effected by topography, spectra can still be acquired from any location of the sample that is at least partially illuminated. Unless the topographic contrast or charging depends on the photon energy, and hence would result in artifacts, any spectrum can in principle be normalized to the carbon edge continuum and quantitative analysis on a per carbon atom basis can be performed. We present spectra in Fig. 4 from various locations on the samples, including several locations along the spines and intersections as indicated by the boxes in Fig. 3. While these spectra have not been normalized to the carbon edge continuum, they clearly show that there is no spectral intensity at the C-Br shifted C-1s to π^* energy of 286.3 eV that is characteristic of PBrS. Hence, the surface is pure PS everywhere on the sample within the characteristic probing depth of NEXAFS PEEM of about 10-20 nm. We have also found that the PBrS is encapsulated in blends that have been annealed. The

encapsulation of PBrS is consistent with the thermodynamically favored state where PS, the component with the lower surface energy segregates to the film surface⁴.

In general, the dewetting process in thin polymer bilayers can consist of diffusive and flow processes both parallel and perpendicular to the polymer/polymer interface. We can obtain an estimate of the relative magnitude of these processes, i.e. diffusion/flow of the PBrS and PS along the PBrS/PS interface and PS perpendicular to the interface from figure 5, where we show area averaged PEEM spectra of bilayer samples annealed for 1 day, 2 days, and 11 days. These spectra clearly show that encapsulation does not occur immediately at the onset of dewetting. After two days of annealing, the PBrS layer has already moved parallel to the PS interface to form holes, several microns in diameter, exposing the underlying PS at numerous places [Slep, 1998 #1094]. The lateral distance traveled by the PBrS along the polymer/polymer interface is much larger than the PBrS film thickness (approx. 40nm), yet the PS encapsulation, which requires perpendicular diffusion over a distance approx. the thickness of the PBrS overlayer, has not yet occurred. This is illustrated in figure 5, where we can see that the area-averaged spectrum after 2 days is still dominated by the PBrS overlayer. Encapsulation is essentially complete after annealing for 11 days (figure 4). This indicates that the diffusion/flow parallel to the interfaces is much faster for both PS and PBrS than the diffusion of PS perpendicular to the PS/PBrS interface. A possible explanation for this phenomenon may be that since the PS and PBrS are highly immiscible, the diffusion of PS through the PBrS layer is severely hindered. The optimum path for encapsulation is then by PS diffusion/flow along the outer surfaces of the dewetting features. Hence the encapsulation process seems to be delayed until the dewetting of the PBrS layer from the PS interface has progressed sufficiently that a significant amount of exposed PS surface area has formed.

In summary, we have used the unique combination of two complementary techniques, PEEM and STXM NEXAFS microscopy, to determine the three dimensional composition of polymer thin films. This allowed us to study both the surface and bulk morphology of PS/PbrS blends and the dewetting dynamics of PS/PbrS bilayers. Our results show that PBrS forms sharply delineated spines that become encapsulated in PS as the PBrS dewets the PS support film. The PS/PBrS contact angle is much larger than the contact angle measured with AFM of the external topographical features. The results demonstrate that the combination of STXM and PEEM is a powerful characterization tool for polymer thin films.

The STXM data was acquired with the X-1A STXM developed by the group of Janos Kirz and Chris Jacobsen at SUNY Stony Brook, with support from the Office of Biological and Environmental Research, DOE contract DE-FG02-89ER60858, and NSF grant DBI-9605045. The zone plates were developed by S. Spector and C. Jacobsen of Stony Brook and D. Tennant of Lucent Technologies Bell

Labs, with support from NSF grant ECS-9510499. The PEEM data was acquired at the Advanced Light Source. The NSLS and ALS are supported by the Office of Basic Energy Sciences, Energy Research, Department of Energy. H. Ade, D.A. Winesett and A.P. Smith are supported by NSF Young Investigator Award DMR-9458060. M. H. Rafailovich and J. Sokolov are supported by NSF DMR-9732230 (MRSEC Program) and DOE-SG02-93-ER45481

Captions:

Fig. 1. Reference spectra of PS and PBrS normalized to the pre and post edge linear absorption coefficients of Henke²³, assuming a density of 1.07 g/cm³ for PS and 1.53 g/cm³ for PBrS²⁴.

Fig. 2. Thickness maps of PBrS/PS bilayer after annealing for 1 week: (a) PS map, (b) PBrS map, and (c) total thickness.

Fig. 3. PEEM image of a 30nm/34 nm PBrS/PS bilayer annealed for 11 days (acquired at 300 eV). A Voronoi tessellation pattern similar to Fig. 2 is clearly visible. The differences in appearance relative to Fig. 2 are due to the different contrast mechanism in a PEEM and a STXM (see text for details). The boxes indicate the areas of which the spectra in Fig. 4 were acquired. The arrow bar equals 20 μ m.

Fig. 4. Point spectra acquired with the PEEM from various locations on the sample as indicated by the boxes in Fig. 3, including several locations right on top of the spines and their intersections.

Fig. 5. Evolution of PBrS peak in PEEM spectra from a 30nm/35nm PBrS/PS bilayer as a function of annealing time.

References:

- ¹J. Genzer and E.J. Kramer, Phys. Rev. Lett. **78**, 4946-4949 (1997).
- ²S. Affrossman, G. Henn, S.A. O'Neill, R.A. Pethrick, and M. Stamm, Macromol **29**, 5010-5016 (1996).
- ³E. Kumacheva, L. Li, M.A. Winnik, D.M. Shinozaki, and P.C. Cheng, Langmuir **13**, 2483-2489 (1997).
- ⁴G. Krausch, E.J. Kramer, M.H. Rafailovich, and J. Sokolov, Appl. Phys. Lett. **64**, 2655-2657 (1994).
- ⁵W. Straub, F. Bruder, R. Brenn, G. Krausch, H. Bielefeldt, A. Kirsch, O. Marti, J. Mlynek, and J.F. Marko, Europhysics Letters **29**, 353-358 (1995).
- ⁶K. Tanaka, A. Takahara, and T. Kajiyama, Macromol **29**, 3232-3239 (1996).
- ⁷S. Wahlheim, M. Boltau, J. Mlynek, G. Krausch, and U. Steiner, Macromol **30**, 4995-5003 (1997).
- ⁸P. Lamboony, K.C. Phelan, O. Haugg, and G. Krausch, Phys. Rev. Lett. **76**, 1110 (1996).
- ⁹S. Qu, C.J. Clarke, Y. Liu, M.H. Rafailovich, J. Sokolov, K.C. Phelan, and G. Krausch, Macromolecules **30**, 3640-3645 (1997).
- ¹⁰K.R. Shull and T.E. Karis, Langmuir **10**, 334-339 (1994).
- ¹¹H. Ade, X. Zhang, S. Cameron, C. Costello, J. Kirz, and S. Williams, Science **258**, 972 (1992).
- ¹²X. Zhang, H. Ade, C. Jacobsen, J. Kirz, S. Lindaas, S. Williams, and S. Wirick, Nucl. Instrum. Meth. in Phys. Res. **A347**, 431-435 (1994).
- ¹³A. Cossy-Favre, J. Diaz, S. Anders, H.A. Padmore, Y. Liu, M. Samant, J. Stohr, H. Brown, and T.P. Russel, Acta Phys. Polonica A **91** (1997).
- ¹⁴A. Cossy-Favre, J. Diaz, Y. Liu, H. Brown, M.G. Samant, J. Stöhr, A. J. Hanna, S. Anders, and T.P. Russell, Macromol. ((in press)).
- ¹⁵E.G. Rightor, A.P. Hitchcock, H. Ade, R.D. Leapman, S.G. Urquhart, A.P. Smith, G. Mitchell, D. Fisher, H.J. Shin, and T. Warwick, J. Phys. Chem. B **101**, 1950-1961 (1997).
- ¹⁶J. Stöhr, *NEXAFS Spectroscopy* (Springer-Verlag, Berlin, 1992).
- ¹⁷H. Ade, Trends Polym. Sci. **5**, 58-66 (1997).
- ¹⁸X. Zhang, R. Balhorn, J. Mazrimas, and J. Kirz, J. Struc. Biol. **116**, 335-344 (1996).
- ¹⁹C. Jacobsen, S. Williams, E. Anderson, M.T. Brown, C.J. Buckley, D. Kern, J. Kirz, M. Rivers, and X. Zhang, Opt. Commun. **86**, 351 (1991).
- ²⁰B. Tonner, D. Dunham, T. Droubay, and M. Pauli, J. Electron Spectros. Relat. Phenom. **84**, 211-229 (1997).

- ²¹T.G. Stange, R. Mathew, D.F. Evans, and W.A. Hendrickson, *Langmuir* **8**, 920-928 (1992).
- ²²W. Zhao, X. Zhao, M.H. Rafailovich, T.M. J. Sokolov, R.S. Stein, R.C. Composto, E.J. Kramer, R.A.L. Jones, M. Sansone, and M. Nelson, *Physica B* **173**, 43 (1991).
- ²³B.L. Henke, E.M. Gullikson, and J.C. Davis, *At. Data Nucl. Data Tables* **54**, 181-342 (1993).
- ²⁴J.E. Mark, *Physical Properties of Polymers Handbook* (Woodbury, New York, 1996).




Fig. 1. H. Ade et al. "Bulk ..."




Fig. 2. H. Ade et al. "Bulk ..."




Fig. 3. H. Ade et al. "Bulk ..."




Fig. 4. H. Ade et al. "Bulk ..."




Fig. 5. H. Ade et al. "Bulk ..."

ERNEST ORLANDO LAWRENCE BERKELEY NATIONAL LABORATORY
ONE CYCLOTRON ROAD | BERKELEY, CALIFORNIA 94720