

Lawrence Berkeley National Laboratory

Recent Work

Title

CALORIMETRIC EVIDENCE FOR A SINGLET GROUND STATE IN CuCr AND CuFe

Permalink

<https://escholarship.org/uc/item/97z3w7bg>

Authors

Triplett, B.B.
Phillips, Norman E.

Publication Date

1971-09-01

c.1

RECEIVED
LAWRENCE
RADIATION LABORATORY

OCT 22 1971

LIBRARY AND
DOCUMENTS SECTION


CALORIMETRIC EVIDENCE FOR A
SINGLET GROUND STATE IN CuCr AND CuFe

B. B. Triplett and Norman E. Phillips

September 1971

AEC Contract No. W-7405-eng-48

For Reference
Not to be taken from this room



DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

Calorimetric Evidence for a Singlet Ground
State in CuCr and CuFe[†]

B. B. Triplett and Norman E. Phillips*

Inorganic Materials Research Division of the Lawrence Berkeley Laboratory,
and Department of Chemistry; University of California,
Berkeley, California 94720

Abstract

Heat capacity measurements show that the entropy reduction associated with the formation of the spin compensated state in CuCr is $R \ln (2S + 1)$. The magnetic field dependence of the heat capacity of CuFe suggests that at $T \ll T_K$ the susceptibility has the form $\chi = \chi_0 [1 - 15(T/T_K)^2]$, which is consistent with the third law of thermodynamics.

The ground state of a single magnetic impurity in a metal continues to be an unsolved problem in spite of the attention it has received. Different theories give different physical pictures for the ground state and make different predictions for the 0 K entropy and the temperature dependences of physical properties at $T \ll T_K$, where T_K is the Kondo temperature.¹ Heat capacity measurements on both CuFe and CuCr have been interpreted as showing that ΔS , the entropy reduction associated with the formation of the spin-compensated state, is less than $R \ln(2S + 1)$.^{2,3} In the same systems, the temperature dependence of the magnetic susceptibility²⁻⁵ χ , if extrapolated to $T = 0$, does not satisfy the third law of thermodynamics requirement $[\partial\chi/\partial T]_{T=0} = 0$. This also implies that the spin degeneracy is not completely removed at $T = 0$. We report here new heat capacity measurements on CuCr and an extension of earlier measurements⁶ on CuFe to higher temperatures. In the single-impurity limit the new data show that the heat capacity anomalies are broader than had been indicated by earlier measurements. The CuCr data are well represented by the Bloomfield-Hamann theory for $T/T_K > 0.07$ and gives $\Delta S = R \ln(2S + 1)$. The CuFe data are consistent with $\Delta S = R \ln(2S + 1)$. Their field dependence shows that the low-temperature single-impurity χ deviates from an extrapolation of the above 1 K data^{4,5} in the direction required by the third law, and suggests that $\chi = \chi_0 [1 - 15(T/T_K)^2]$ at $T \ll T_K$.

The Cr content of the CuCr samples was determined to $\pm 5\%$ by a spectrophotometric method.⁸ Within that accuracy the 4.2 K resistivities were fitted by $\rho_{4.2}/c = 1.08 \times 10^{-3} \mu \Omega\text{-cm/at ppm}$ where c is the concentration, and that relation was used to assign the reported concentrations

from values of $\rho_{4.2}$. The CuFe samples were the same ones used in an earlier investigation.⁶ All measurements were made with a reproducible germanium thermometer that permitted a high sample-to-sample precision. The heat capacities of the sample holder and the pure copper from which the samples were made were measured in separate experiments.

The zero-field CuCr data are shown in Fig. 1 as ΔC , the heat capacity in excess of that of pure copper divided by the concentration. Within the precision of the measurements, $\Delta C \propto c$, as it must be in the single impurity limit, except below 0.15 K. At the lowest temperatures the 51 at ppm sample exhibits effects of impurity-impurity interactions similar to those observed⁶ in CuFe. The dashed curve represents a linear extrapolation to $T = 0$ as suggested by measurements^{6,9} on CuFe at lower reduced temperatures. Above 0.15 K there are no systematic differences between the samples, and we have taken the 51 ppm data, for which the precision is best, as defining the shape of the peak. The peak is better defined than in earlier work³ and is broader. The solid curve represents the theory of Bloomfield and Hamann,⁷ scaled and shifted in temperature to fit the peak. As drawn it corresponds to $T_K = 2.1$ K, and provides an excellent fit to the data for $T/T_K > 0.07$. The linear extrapolation to $T = 0$ and extrapolation to high temperature by the theoretical curve give $\Delta S = 1.05 R \ln 4$. Since the spin is $3/2$,¹⁰ this corresponds to the complete removal of the degeneracy, to within the uncertainty in the concentrations.

For 81 and 195 at ppm CuFe $\Delta C/c$ is independent of concentration for $T > 0.12$ K. The maximum $\Delta C/c$, which occurs near 9 K, is greater than

that found by Franck, Manchester, and Martin¹¹ for more concentrated samples, but is consistent with the trend in their data. At higher temperatures the lattice heat capacity obscures the shape of ΔC , but an extrapolation to $T = \infty$ with a Bloomfield-Hamann curve adjusted to fit the data near the peak in ΔC , which requires $T_K = 28$ K, gives $\Delta S = 1.01 R \ln 4$. In this case approximately 50% of the entropy is under the extrapolation, but by analogy with CuCr it seems probable that the entropy is $R \ln 4$. The significance of the new data is in showing that the anomaly is broader than that observed at higher concentrations, and that there is probably a greater contribution to ΔS at high temperatures.

The heat capacities of 81 and 640 at ppm CuFe samples in magnetic fields are shown in Figs. 2 and 3. The data for the 81 at ppm sample in low fields were indistinguishable from the zero-field data, and have been omitted for clarity. Measurements on a 195 at ppm sample have shown that $\Delta C/c$ is the same as for the 81 at ppm sample for the fields and temperatures in Fig. 2. The dependence of $\Delta C/c$ on magnetic field shown in Fig. 2 is therefore characteristic of single-impurity behavior. In Fig. 3 the dashed curve represents the single-impurity zero-field limit established by measurements at lower concentrations.^{6,9} The zero-field heat capacity in excess of that represented by the dashed curve is not proportional to concentration and must therefore be associated with impurity-impurity interactions.⁶ The application of a magnetic field broadens the interaction contribution to ΔC and shifts it to higher temperatures. Qualitatively, the effect of magnetic field on ΔC for the 640 at ppm sample can be easily understood. In zero field uncompensated spins contribute

to ΔC at temperatures corresponding to the effective fields (generated by other uncompensated spins) they experience. For the 640 at ppm sample the zero field heat capacity shows that these fields are $\lesssim 1.5$ kOe.⁶ In an applied field greater than this value their contribution to ΔC is shifted to higher temperatures. In 38 kOe it is almost entirely determined by the applied field and occurs at temperatures above 1 K. Thus, the reduction of $\Delta C/c$ at low temperatures by a 38 kOe applied field is the sum of two effects -- the shift of the impurity-impurity interaction contribution to higher temperatures and the small reduction of the impurity-conduction electron interaction contribution shown by the data for the 81 at ppm sample.

The field dependence of the heat capacity is related to the temperature dependence of the magnetization M by the thermodynamic equality

$$\frac{\partial(C/T)}{\partial H} = \frac{\partial^2 M}{\partial T^2} = H \frac{\partial^2 \chi}{\partial T^2}, \quad (1)$$

where $\chi = M/H$. At temperatures below 1 K the differential susceptibility of dilute CuFe is the sum of a $T^{-\frac{1}{2}}$ term that saturates in fields of the order of 1 kOe and a constant term.² M is therefore the sum of a $T^{-\frac{1}{2}}$ term that is independent of field in high field and a temperature independent term. The large positive values of $\partial(C/T)/\partial H$ predicted by Eq.(1) for the $T^{-\frac{1}{2}}$ term are observed, but only in regions of c and T where interaction effects are important. They are apparent in Fig. 3, for example, for $H \approx 1$ kOe and $0.4 < T < 1.5$ K. In a 195 at ppm sample they occur at lower temperatures and correspondingly lower fields. For the 81 at ppm sample they presumably occur at very low temperatures and

fields where they are lost in the scatter of the data. Since the positive values of $\partial(C/T)/\partial H$ are not proportional to c they cannot be associated with the impurity-conduction electron interaction. We conclude that they, and the associated $T^{-\frac{1}{2}}$ susceptibility, are a consequence of impurity-impurity interactions and are not characteristic of the spin-compensated state. Similar conclusions have been drawn from the concentration dependence of the susceptibility.^{5,12}

Above 1.3 K the single-impurity susceptibility, established by a careful study of the concentration dependence,⁵ has the form $\chi = \chi_0 \cdot 29/(T + 29)$. Substitution of this expression into Eq.(1) gives a small positive value of $\partial(C/T)/\partial H$ and an effect on ΔC comparable to the scatter in the data for 38 kOe. This is in agreement with the experimental $\Delta C/c$ for 81 at ppm above approximately 2 K. At lower temperatures, however, the larger negative observed values of $\partial(C/T)/\partial H$ require a change in the curvature of χ vs. T . The change is in the direction suggested by the third law of thermodynamics which requires $[\partial\chi/\partial T]_{T=0} = 0$. Thus, there is a clear indication that near $T_K/15$ the temperature dependence followed by χ over a wide range of higher temperatures^{4,5} is modified in the direction required by the third law. Theoretical evidence for an effect of this type has recently been reported.¹³ If the third law is assumed, the field dependence observed below 0.7 K, $\partial(C/T)/\partial H \propto \text{constant} \times H$, can be integrated to give $\chi = \chi_0[1 - 15(T/29)^2]$. Below 2 K the difference between this expression and $\chi = \chi_0 \cdot 29/(T + 29)$ is less than 2% and would not have been observed in the direct susceptibility measurements,⁵ which are dominated by the copper nuclear susceptibility below 1.3 K. The

field dependence of the heat capacity, however, is very sensitive to the difference between the two expressions because it measures $\partial^2\chi/\partial T^2$, which is very different for the two expressions.

The form suggested for the temperature dependence of χ in the low-temperature single-impurity limit is particularly interesting in connection with other recent experimental results. For $T \ll T_K$, $C \propto T^{6,9}$ and recent measurements on the resistivity ρ of very dilute CuFe show¹⁴ that $\rho = \rho_0 [1 - \beta(T/T_K)^2]$ where β is a constant. Thus, for CuFe, a pattern is emerging for the temperature dependences of physical properties at $T \ll T_K$ that is very different from that of a few years ago. Recent results on AuV suggest the same pattern.^{14,15} It is also interesting that several theoretical treatments of the Kondo effect predict this pattern, or parts of it.¹

References

† Work supported by the U.S. Atomic Energy Commission

* On leave 1970-71 at Department of Technical Physics, Technical University of Helsinki, Otaniemi (Helsinki), Finland.

1. The theory has been recently reviewed by J. Kondo in Solid State Physics, edited by F. Seitz, D. Turnbull, and H. Ehrenreich (Academic Press, New York, 1969) Vol. 23, p. 183, and by A. J. Heeger, *ibid.*, p. 283.
2. M. D. Daybell, W. P. Pratt, Jr., and W. A. Steyert, *Phys. Rev. Letters* 21, 353 (1968).
3. M. D. Daybell, W. P. Pratt, Jr., and W. A. Steyert, *Phys. Rev. Letters* 22, 401 (1969).
4. C. M. Hurd, *Phys. Rev. Letters* 18, 1127 (1967).
5. J. L. Tholence and R. Tournier, *Phys. Rev. Letters* 25, 876 (1970).
6. J. C. F. Brock et al., *Solid State Comm.* 8, 1139 (1970).
7. P. E. Bloomfield and D. R. Hamann, *Phys. Rev.* 164, 856 (1967).
8. The analyses were carried out by Mr. R. D. Giaque of the Lawrence Berkeley Laboratory.
9. New measurements (with a germanium thermometer) show that $\Delta C \propto T$ for the 81 at ppm CuFe sample to the lowest temperature, 0.06 K; and that $\Delta C/c$ is the same for the 81 at ppm sample and the 195 at ppm sample above 0.12 K. B. B. Triplett and Norman E. Phillips, to be published.

10. P. Monod and S. Schultz, Phys. Rev. 173, 645 (1968).
11. J. P. Franck, F. D. Manchester, and Douglas L. Martin, Proc. Roy. Soc. (London), A263, 494 (1961).
12. E. C. Hirschkoﬀ, M. R. Shanabarger, O. G. Symko, and J. C. Wheatley, Phys. Letters 34A, 341 (1971).
13. K. D. Schotte and U. Schotte (to be published).
14. W. M. Star and B. M. Boerstoeel, Phys. Letters 29A, 26 (1969).
15. B. M. Boerstoeel and W. M. Star, Phys. Letters 29A, 97 (1969);
J. E. van Dam and P. C. M. Gubbens, Phys. Letters 34A, 185 (1971).

LEGAL NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

TECHNICAL INFORMATION DIVISION
LAWRENCE RADIATION LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720